



AEROSPACE MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N. Y. 10017

AMS7493E

Issued 6-1-51
Revised 3-15-66

RINGS, FLASH WELDED Non-Austenitic Corrosion Resistant Steels

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** Primarily for parts such as flanges and rings, requiring corrosion and moderate heat resistance, fabricated by flash welding non-austenitic corrosion resistant steels, usually AMS 5613, AMS 5614, AMS 5615, AMS 5616, or AMS 5627.
3. **MATERIAL:** Material from which rings are made shall be as specified on the drawing.
4. **FABRICATION:**
 - 4.1 **Forming:** Rings as applicable for the particular parts shall be formed from suitably rolled, extruded, or forged shapes.
 - 4.2 **Preparation for Welding:** Formed rings shall be clean and free from foreign materials in the area of electrode contact and at the surfaces to be welded.
 - 4.3 **Welding:** The ends of the formed rings shall be flash butt-welded together; unless otherwise permitted by purchaser, there shall be only one weld per ring. Welding shall be performed on a machine provided with accurate control of feed of joint during flashing, rate and distance of travel of sections to be welded, secondary voltage and current magnitude, and timing and current cut-off. The flash shall be maintained during the flashing interval of the welding operation. The amount of manual flashing, for purposes of preheating, shall be limited to 10% of total flashing distance. The machine shall be capable of repeating the sequence of operations independently of the skill of the operator. A record of all machine settings and sequence of operations for welding each different ring shall be kept by the vendor and be made available to the purchaser upon written request.
 - 4.4 **Annealing:** The welded rings shall be annealed by heating to 1200 - 1500 F (648.9 - 815.6 C), holding at heat for not less than 1 hr, and cooling in air. Unless otherwise specified, rings made of AMS 5613, AMS 5614, AMS 5615, and AMS 5616 shall be austenitized by heating to not lower than 1750 F (954 C) and not higher than 1850 F (1010 C) and cooled to room temperature before annealing.
 - 4.4.1 For rings less than 0.188 in. in thickness, austenitizing and cooling are not required and, when permitted by purchaser, annealing may be performed locally by heating the weld zone to the proper temperature within the range specified in 4.4, holding at heat for 15 - 30 min., and cooling in air.
 - 4.5 **Proof Testing of Welds (Sizing):** Unless otherwise specified, each ring shall have flash and excess metal at the weld removed to within +1/32 in. of parent metal surfaces, and shall then be sized. Flash may be removed from rings either before or after annealing as in 4.4. Preliminary sizing may be done before cooling, but final sizing shall be done at room temperature. The stress applied for final sizing shall be sufficient to provide a permanent expansion of not less than 1% across a 2 in. gage length centered on the weld. Sizing shall be performed in such a way as to provide uniform stress distribution throughout the ring.

SAE Technical Board rules provide that: "All technical reports, including standards approved by the Board, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 4.5.1 For rings made of material less than 0.188 in. thick, flash removal may reduce thickness below that of parent metal provided that the finished weld blends smoothly into adjacent metal and provided that thickness is not reduced below the minimum specified on the drawing for the parent metal; when so specified by purchaser, proof testing of such rings will be waived if welding precedes a final forming operation which involves an expansion of the weld equivalent to or exceeding that required by 4.5.
- 4.6 When the drawing or applicable material specification requires additional heat treatment after annealing, rings shall be so heat treated after sizing.
- 4.7 Restoration to Shape: If it is necessary to restore shape of rings following sizing, or following final heat treatment when specified, such operation shall be done on suitable presses and not by localized blows as from a hammer. Rings may be reheated for such operation but shall not be heated to a temperature higher than any prior tempering temperature.
- 4.8 Any descaling requirement shall be as agreed upon by purchaser and vendor.

5. TECHNICAL REQUIREMENTS:

- 5.1 Test specimens cut, after final heat treatment of the lot, from welded rings processed to this specification shall conform to the following requirements. When permitted by purchaser, rings to be supplied with additional heat treatment after annealing may be tested in the annealed condition by the vendor, but the final basis for acceptance or rejection shall be tests made on fully heat treated rings.

5.1.1 Rings Having Specified Maximum Hardness Up To Brinell 241, Incl, or Equivalent:

Ø	Tensile Strength	
	Through Welded Area	90% min of parent metal in same ring
Ø	Elongation, % in 2 in. or 4D	
	Through Welded Area	60% min of parent metal in same ring

5.1.2 Rings Having Specified Maximum Hardness Higher Than Brinell 241 or Equivalent:

Ø	Tensile Strength	
	Through Welded Area	90% min of parent metal in same ring
Ø	Elongation, % in 2 in. or 4D	
	Through Welded Area	50% min of parent metal in same ring

- 5.2 Hardness: Rings shall have hardness not higher than Brinell 241 or equivalent, unless otherwise specified in the applicable material specification or on the drawing or purchase order.

6. QUALITY:

- 6.1 Parts shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or performance. Any controlled grain size requirement shall be as agreed upon by purchaser and vendor.
- 6.2 Parts shall be subject to non-destructive testing as agreed upon by purchaser and vendor.

7. REPORTS:

- 7.1 Unless otherwise specified, the vendor of welded rings shall furnish with each shipment three copies of a report of the results of tests for tensile properties and hardness of each lot in the shipment. This report shall include the purchase order number, this specification number, material specification number, contractor or other direct supplier of material, size or part number, heat number, and quantity from each lot. When material for making rings is produced or purchased by the ring vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of the applicable material specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.