

**AEROSPACE
MATERIAL
SPECIFICATION**

AMS 7718B
Superseding AMS 7718A

Issued 1-15-61
Revised 1-1-82

**MAGNETIC ALLOY BARS, TUBING, AND FORGINGS
50Ni - 50Fe**

1. SCOPE:

- 1.1 Form: This specification covers a magnetic nickel-iron alloy in the form of bars, rods, tubing, forgings, and forging stock.
- 1.2 Application: Primarily for parts used in magnetic circuits requiring high magnetic permeability and saturation induction after high temperature annealing in hydrogen.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2241 - Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
- AMS 2243 - Tolerances, Corrosion and Heat Resistant Steel Tubing
- AMS 2350 - Standards and Test Methods
- AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock
- AMS 2374 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Forgings and Forging Stock
- AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistant Steels and Alloys
- AMS 2808 - Identification, Forgings

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A341 - Direct-Current Magnetic Properties of Materials Using
D-C Permeameters and the Ballistic Test Methods

ASTM E18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic
Materials

- 2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

- 2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall be an alloy containing approximately 50% nickel and 50% iron with other alloying elements in such proportions as required to provide a product meeting the requirements of 3.3.

- 3.2 Condition: The product shall be supplied in the following condition:

- 3.2.1 Bars, Rods, and Tubing: Cold drawn; standards for acceptance of surface appearance shall be as agreed upon by purchaser and vendor.

- 3.2.2 Forgings: As ordered.

- 3.2.3 Forging Stock: As ordered by the forging manufacturer.

- 3.3 Properties: The product shall conform to the following requirements:

- 3.3.1 Hardness: Shall be as follows, determined in accordance with ASTM E18:

- 3.3.1.1 Bars and forgings 0.50 in. (12.5 mm) and under in nominal diameter or
Ø cross-sectional thickness shall have hardness not lower than 90 HRB.

- 3.3.1.2 Bars and forgings over 0.50 in. (12.5 mm) in nominal diameter or
Ø cross-sectional thickness shall have hardness not lower than 75 HRB.

- 3.3.2 Magnetic Properties: Shall be as follows, determined in accordance with ASTM A341 on specimens as in 4.3.1 annealed by heating to $2150^{\circ}\text{F} + 25$ ($1175^{\circ} + 15$) in a dry hydrogen atmosphere having a dew point of -60°F (-50°C) or lower, holding at heat for $4 \text{ hr} + 0.25$, and cooling in a nonoxidizing atmosphere at a rate not greater than $100 \text{ F (55 C) deg per hr}$ to $1100^{\circ}\text{F (595}^{\circ}\text{C)}$ or lower or at a cooling rate recommended by the alloy producer:

3.3.2.1 Maximum Permeability, min

Nominal Diameter or Distance
Between Parallel Sides

Inches	(Millimetres)	
Up to 5/16, excl	(Up to 7.9, excl)	40,000
5/16 and Over	(7.9 and Over)	20,000

3.3.2.2 Permeability at 100 Gauss (0.01T), min

Nominal Diameter or Distance
Between Parallel Sides

Inches	(Millimetres)	
Up to 5/16, excl	(Up to 7.9, excl)	6,000
5/16 and Over	(7.9 and Over)	4,000

3.3.2.3 Induction at 100 Oersteds (7958 A/m), min
15 gauss (1.5mT)

3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.

3.5 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars, rods, and tubing will be acceptable in mill lengths of 6 - 20 ft (2 - 6 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).

3.6 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of the following:

3.6.1 Bars and Rods: AMS 2241.

3.6.2 Tubing: AMS 2243.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirement of this specification.

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling: Shall be in accordance with the following; a lot shall be all product of the same nominal diameter or distance between parallel sides from the same heat of alloy:

4.3.1 Bars, Rods, and Tubing: AMS 2371.

4.3.2 Forgings and Forging Stock: AMS 2374.

4.3.3 Samples for magnetic properties (3.3.2) testing shall, unless otherwise specified, be selected in accordance with either 4.3.3.1 or 4.3.3.2; the sampling method used shall be reported with the test results.

4.3.3.1 A pilot sample nominally 0.014 in. (0.35 mm) thick from each heat of alloy.

4.3.3.2 A sample taken at random from finished product of the same nominal thickness from the same heat of alloy.

4.4 Reports:

4.4.1 The vendor of the product shall furnish with each shipment three copies of a report showing the method of sampling for magnetic properties and the results of tests for hardness of each lot and the magnetic properties of each heat. This report shall include the purchase order number, heat number, AMS 7718B, cooling rate if other than 100 F (56 C) deg per hr, thickness of sample used for magnetic properties testing, size, and quantity from each heat. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, AMS 7718B, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification and shall include in the report either a statement that the material conforms or copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with the following:

4.5.1 Bars, Rods, and Tubing: AMS 2371.

4.5.2 Forgings and Forging Stock: AMS 2374.