

AEROSPACE MATERIAL SPECIFICATION



AMS 7879D

Issued NOV 1970
Revised JAN 2002
Reaffirmed JUL 2006

Superseding AMS 7879C

Tungsten Carbide-Cobalt Powder Cast and Crushed

1. SCOPE:

1.1 Form:

This specification covers tungsten carbide-cobalt in the form of powder.

1.2 Application:

This powder has been used typically for producing plasma spray coatings to provide wear and fretting resistant surfaces, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order form a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19248-2959 or www.astm.org.

ASTM B 214 Sieve Analysis of Granular Metal Powders

ASTM B 215 Sampling Finished Lots of Metal Powders

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: custsvc@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	3.90	4.30
Cobalt	10.00	12.00
Iron	--	2.00
Tungsten	remainder	

3.2 Condition:

As manufactured.

3.3 Properties:

Powder shall conform to the following requirements:

- 3.3.1 Particle Size Distribution: Powder shall be supplied with the following particle size distribution. Sieve analysis shall be conducted in accordance with ASTM B 214; subsieve (micron) analysis shall be conducted in accordance with a method approved by purchaser.

TABLE 2 - Particle Size Distribution

Mesh or Micron Size*	Percent By Weight min	Percent By Weight max
-270 mesh (46 μ m)	100.0	--
+325 mesh (45 μ m)	--	0.5
- 20 μ m	70.0	--
- 5 μ m	--	10

* + indicates retained on sieve
- indicates passing through sieve

- 3.3.2 Plasma Spraying: Powder shall produce acceptable spray coatings; standards for acceptance and method of test shall be agreed upon by purchaser and vendor.

3.4 Quality:

Powder, as received by purchaser, shall be thoroughly blended, uniform in color and quality, dry, and free from foreign materials and from imperfections detrimental to its spraying qualities.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of powder shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the powder conforms to the specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: All technical requirements except 3.3.2 (plasma spraying) are acceptance tests, and shall be performed on each heat or lot as applicable.

4.2.2 Preproduction Tests: All technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of powder to a purchaser, on each lot, when a change in ingredients and/or processing requires approval by the cognizant engineering organization (see 4.4.2), and when purchaser deems confirmatory testing to be required.

4.3 Sampling and Testing:

Shall be in accordance with ASTM B 215; sufficient powder shall be taken from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.

4.3.1 When a statistical sampling plan has been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3 and the report of 4.5 shall state that such plan was used.

4.4 Approval:

4.4.1 The process and control procedures, a preproduction sample, or both, whichever is specified, shall be approved by the cognizant engineering organization before production powder is supplied.

4.4.2 The supplier shall make no significant change in ingredients, processes, or controls from those on which the approval was based, unless the change is approved by the cognizant engineering organization. A significant change is one which, in the judgment of the cognizant engineering organization, could affect the properties or performance of the powder.

4.5 Reports:

The vendor of powder shall furnish with each shipment a report showing the results of tests for chemical composition and particle size distribution of each lot and stating that the powder conforms to the other technical requirements. This report shall include the purchase order number, lot number, AMS 7879D, vendor's product designation, and quantity.

4.6 Resampling and Retesting:

If any sample used in the above tests fails to meet the specified requirements, disposition of the powder may be based on the results of testing three additional samples for each original nonconforming sample. Failure of any retest sample to meet the specified requirements shall be cause for rejection of the powder represented. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Packaging and Identification:

5.1.1 Powder shall be packaged in 5-pound (2.5-kg) sealed containers to protect it from contamination during shipment and under normal dry storage conditions. Seals used on containers shall be so designed that they must be destroyed in order for the container to be opened.

5.1.2 Each individual container shall be legibly identified with not less than the following information, using characters which will not be obliterated by normal handling:

TUNGSTEN CARBIDE-COBALT POWDER

AMS 7879D

MANUFACTURER'S IDENTIFICATION _____

PURCHASE ORDER NUMBER _____

QUANTITY _____

LOT NUMBER _____

5.1.3 Containers of powder shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the powder to ensure carrier acceptance and safe delivery.

6. ACKNOWLEDGMENT:

A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS:

Powder not conforming to this specification, or to modifications authorized by purchaser, will be subject to rejection.