

AEROSPACE RECOMMENDED PRACTICE

SAE ARP1785

REV.
A

Issued 1981-08
Revised 2000-10

Superseding ARP1785

Standard Codes for Sleeving on PTFE Hose Assemblies

FOREWORD

Changes in this revision are format/editorial only.

1. SCOPE:

This document provides a standard reference list of code designations to be applied to the various sleeves used on TFE hose assemblies when preparing related "AS" specifications and part numbers

2. TITLE:

Standard Codes for sleeving to be used on PTFE Hose Assemblies.

3. CODES:

TABLE 1

<u>Sleeving Code</u>	<u>Type of Sleeving</u>	<u>Temperature Limit</u>	
-	Hose Only	400°F	204°C
A	Abrasion Sleeve Tubular (TFE-AS1291-B)	400°F	204°C
B	Abrasion Sleeve Coil (Nylon AS1294)	275°F	135°C
C	Firesleeve SIL-FG (15 Min) AS1072	400°F	204°C
D	Abrasion Sleeve Integral Silicone Composite	350°F	177°C
E	Abrasion Sleeve Shrink-on (FEP)	350°F	177°C
F	Abrasion Sleeve Shrink-on (Polyolefin AS1073B)	275°F	135°C
G	Firesleeve SIL-FG (5 Min) AS1072	400°F	204°C
H	Firesleeve Integral Silicone (15 Min)	400°F	204°C
J	Firesleeve Integral Silicone (5 Min)	400°F	204°C
K	Abrasion Sleeve (Braided) Polyester	300°F	149°C
L	Abrasion Sleeve Coil (PTFE-AS1293)	400°F	204°C
M	Abrasion Sleeve Coil (Butyrate-AS1292)	275°F	135°C
N	Firesleeve SIL-FG (15 Min) AS1072 Snug Fit	400°F	204°C

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

TO PLACE A DOCUMENT ORDER: (724) 776-4970

FAX: (724) 776-0790

SAE WEB ADDRESS: <http://www.sae.org>