



400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE RECOMMENDED PRACTICE

SAE ARP4915

Issued 1997-11

Submitted for recognition as an American National Standard

DISPOSITION OF LANDING GEAR COMPONENTS INVOLVED IN ACCIDENTS/INCIDENTS

1. SCOPE:

This document establishes a procedure for disposition of landing gear components that have been involved in accidents/incidents. The recommendations in this document apply to high heat treat steel components (FTU = 180 ksi and above).

2. REFERENCES:

- 2.1 British Civil Aviation Authority, Airworthiness Notice No. 97 (Issue 1, May 10, 1982) Return to Service of Aircraft Items Recovered From Aircraft Involved in Accidents/Incidents
- 2.2 MIL-H-6875, Heat Treatment of Steel, Process for
- 2.3 FAA Advisory Circular 21-38, Disposition of Unsalvageable Aircraft Parts and Materials

3. DEFINITIONS:

3.1 RESIDUAL STRESS:

Stress present in a component that is free of external forces or thermal gradients.

3.2 RESIDUAL STRAIN:

Plastic deformation that remains permanently after removal of the load that caused it.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1997 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:

(412) 772-8510
(412) 776-4970

FAX: (412) 776-0243
FAX: (412) 776-0790

SAE ARP4915**4. IDENTIFICATION OF DAMAGE:**

- 4.1 Landing gear components involved in accidents/incidents can be classified under four different types.

Type I: Components with visible severe mechanical damage (gouged, pierced, etc.).

Type II: Components involved in abnormal heat (fire, frictional heat caused by aborted take-off/hard landing), and when damage is suspected due to a failed wheel bearing.

Type III: Components with visible or measurable dimensional distortion.

Type IV: Components with no visible or measurable defect, but known to have been involved in an accident/incident (no heat damage).

These types of damage are not normally identified in repair and overhaul manuals; therefore separate dispositions are required. A damage assessment is essential to determine the applicable category.

5. DISPOSITION:**5.1 Type I:**

These components are to be considered scrap unless subjected to detail evaluation by cognizant engineers and approved by the airworthiness authorities. However, if the components are to be returned to service, it is strongly recommended to follow steps shown for types II, III, and IV to ensure the removal of residual stresses.

5.2 Type II:

Type II damage will likely cause a reduction in strength, ductility, fatigue properties and/or stress corrosion cracking, due to changes in material properties. The severity of damage caused by intense heat cannot be accurately evaluated with normal shop procedures. Investigation by approved engineering personnel is essential.

NOTE: Do not remove any paint, primer or plating and do not apply any chemicals prior to the investigator viewing the part. Essential evidence may be lost.

Examination of cadmium coated surfaces for evidence of blistering and any color change to primer and enamel, together with accurate testing methods involving hardness and non-destructive methods are required for the proper assessment of damage. Examination of other coatings (such as chrome) for evidence of discoloration is also essential. Unless a thorough investigation is performed, these components are not to be returned to service. For components exposed to local heating effects, a local nital etch inspection is required.

SAE ARP4915**5.2 (Continued):**

The following are the recommended steps when investigating a type II damage:

- a. The part should be thoroughly cleaned using solvent or detergent and water. Abrasives or chemicals which may bleach or discolor must be avoided.
- b. Prior to stripping the part:
 1. Examine primer or painted surfaces for color changes or blistering.
 2. Examine cadmium coated surfaces for blistering.
 3. Examine other coatings (such as chrome) for evidence of discoloration.
- c. Based on the evidence found during the initial examination the following other steps may need to be undertaken:
 1. Remove all bushings and finishes.
 2. Partially or completely strip the part.
 3. Perform a nital or ammonium persulphate etch.
 4. Hardness and other non-destructive tests.
- d. Parts which required etch, hardness, or non-destructive testing should be re-shot-peened to the original manufacturing requirements. Parts which have been nital etched should be stress relieved before shot peening.

WARNING: Unless a thorough investigation by properly qualified personnel is performed, these parts are not to be returned to service.

5.3 Type III:

Any measurable dimensional distortion indicates that the component has been subjected to loads in excess of its material yield limits. Residual stress will reduce its effective strength even if its function is not affected. In addition, straightening the component will contribute to an increase of the residual stress level and will reduce the part resistance to fatigue cracking due to the two cycles of reversed bending overload.

The recommended minimum requirements to reduce residual stresses are:

- a. From the inspection report on the subject component, determine if the part is functionally acceptable.
 1. If the part is functionally unacceptable, it should be considered scrap. Cold working a deformed part is structurally unacceptable.
 2. If the part is functionally acceptable, rework per steps (b thru i).
- b. Remove all bushings and finishes. The part should be completely stripped.

SAE ARP4915**5.3 (Continued):**

- c. Bake at 50 °F below material tempering temperature for 24 h. MIL-H-6875 can be used as a guide to locate material tempering temperature.
- d. Magnetic particle inspect
- e. Nital or ammonium persulphate etch inspect.
- f. Bake at 50 °F below tempering temperature for 24 h.
- g. Hardness test inspect.
- h. Store for an extended period (a minimum of 6 months is recommended).
- i. Magnetic particle inspect.
- j. Re-shot peen entire component to the original manufacturing specifications. Qualification of the shot peening technique is essential since component is to be brought to original drawing requirements.

Due to the embrittling effect of cadmium, chrome, and nickel plating, if excessive tensile residual stresses are still present after the residual stress reduction procedures, the component may fail during the plating procedures.

5.4 Type IV:

Although these components will appear to be sound, residual stresses may be present due to local yielding of the material (overload condition). It is, therefore, important to ensure that such residual stresses are minimized prior to returning the components to service.

To verify the parts are free of deformation, a complete dimensional verification is required. The availability of the engineering drawings is essential, since repair and overhaul manuals will not provide all dimensions and geometrical tolerances. If available, a comparison against original manufacturing dimensions is preferable.

Any deformation found will result in classifying the component as in the type III category.

However, in the absence of sufficient engineering data, it is recommended that the disposition of components with this type of defect be the same as for the type III above.