



AEROSPACE RECOMMENDED PRACTICE

ARP5316

REV. D

Issued 1998-11
Revised 2014-10

Superseding ARP5316C

Storage of Elastomer Seals and Seal Assemblies Which
Include an Elastomer Element Prior to Hardware Assembly

RATIONALE

This revision addresses the users' request to add an additional Table summarizing shelf life for polymer type and explains how to correctly calculate elastomer age.

1. SCOPE

This SAE Aerospace Recommended Practice (ARP) addresses the general requirements for data recording procedures, packaging, and storing of elastomeric seals and seal assemblies which include an elastomeric element prior to the seal being assembled into hardware components. It applies specifically to those elastomeric seals and seal assemblies packaged shortly after manufacture. The storage period prior to installation of the elastomeric seals and seal assemblies into hardware components is commonly referred to as shelf life.

The information contained in this ARP is intended to be utilized by those organizations who do not have specific requirements or recommendations already in place for the control of elastomeric seals and seal assemblies. This ARP can be specified in control, storage, and procurement documents. However, when the requirements of this document are in conflict with the customer's requirements or specifications, the requirements of the customer's detailed specification shall govern.

1.1 Disclaimer

This document does not establish limitations or storage times for assembled components nor the operating life of said components.

2. REFERENCES

2.1 Applicable Documents

The following publications form a part of this document to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order. In the event of conflict between the text of this document and references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2014 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/ARP5316D>

2.1.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2817 Packaging and Identification, Preformed Packings

AS1933 Age Controls for Hose Containing Age-Sensitive Elastomeric Material

2.1.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM D1418 Standard Practice for Rubber and Rubber Latices - Nomenclature

2.1.3 Electric Power Research Institute Publications

Available from EPRI, 3420 Hillview Avenue, Palo Alto, CA 94304, www.epri.com.

NP-6608 Shelf Life of Elastomeric Components

2.1.4 U.S. Government Publications

Available from DLA Document Services, Building 4/D, 700 Robbins Avenue, Philadelphia, PA 19111-5094, Tel: 215-697-6396, <http://quicksearch.dla.mil/>.

AFML-TR-67-235 Literature Survey on the Effects of Long-Term Shelf Aging of Elastomer Materials

ANA Bulletin 438 Age Control of Age-Sensitive Elastomeric Items

DOD 4140.27.M Shelf Life Management Manual

MIL-HDBK-695 Rubber Products: Recommended Shelf Life

MIL-STD-1523 Age Control of Age-Sensitive Elastomeric Materials

2.2 Definitions

2.2.1 ELASTOMER: A material that possesses elastic properties and has undergone vulcanization and/or conversion into a finished product.

2.2.2 SEAL: An elastomeric finished product or an assembly with an elastomeric element which prevents the excursion of media on one side of the product from migrating to the other side.

2.2.3 STORAGE LIFE: The maximum period of time, starting from the time of manufacture, that an elastomeric seal element, appropriately packaged, may be stored under specific conditions, after which time it is regarded as unserviceable for the purposes for which it was originally manufactured. The time of manufacture is the time of cure for thermoset elastomers or the time of conversion into a finished product for thermoplastic elastomers.

2.2.2 HARDWARE COMPONENT: The unit in which the elastomeric seal element is placed.

3. BACKGROUND

Listed below is the background information which led to the creation of this Aerospace Recommended Practice.

3.1 MIL-STD-1523

Age control was imposed on elastomers used in critical sealing devices of aircraft hydraulic, lubricating, and fuel systems after World War II. Several different requirements and specifications were implemented in the years following the war until 1958 when ANA Bulletin 438 was released. This bulletin's purpose was to collect all previous requirements for age control in one document and to make it easier for various agencies and contractors to effectively implement age control. However, confusion in interpretations resulted in abuses, cost increases and inconsistently imposed exceptions.

Many other programs were then undertaken to study age control. The results of many of these were summarized in the Air Force report, AFML-TR-67-235. The conclusion of the studies summarized in this report and others that were in progress was that the overall properties of elastomeric materials were much improved over the materials initially evaluated and age control should be made less restrictive. As a result of this information, MIL-STD-1523 was released in 1973 and superseded ANA Bulletin 438. One of the basic requirements of the new document was to provide a cure date limitation of twelve quarters from cure date to acceptance of the seals by the original procuring activity, whether a government agency, a first or second contractor or an organization which assembles seal and hardware kits. In all cases, the use of cure date was intended to provide for good FIFO (First In - First Out) warehousing procedures.

On February 1, 1984, MIL-STD-1523A was issued to supersede MIL-STD-1523. This revision was targeted at eliminating the confusion in interpretation of the previous document. It also extended cure date requirements from 12 quarters to 40 quarters. MIL-STD-1523A controlled the age of elastomers only at time of acceptance by the government. This meant that the cure date of each elastomer had to be known at the time a system was accepted by the government.

Even with the clarifications of MIL-STD-1523A, confusion still existed and the discussion regarding the need for age control continued.

3.2 EPRI NP-6608

In June, 1989, Bruce Boyum and Jerral Rhoads presented an IEEE Paper: "Elastomer Shelf Life: Aged Junk or Jewels" - IEEE Transactions on Energy Conversion, Vol.4, No.2, pp 191-203, June, 1989. After a detailed review of the information from previous studies and the age control documents including MIL-HDBK-695C, they concluded that age control limits were very conservative and shelf life could be extended as long as proper storage conditions were maintained.

This was followed up in May, 1994 by EPRI NP-6608, "Shelf Life of Elastomeric Components". The conclusion of this detailed study was that with proper storage, shelf life for elastomer seals could be extended to 32 years.

3.3 AS1933A

Based upon the data from the numerous studies concerning age control and shelf life, MIL-STD-1523A was canceled on January 30, 1995 - without replacement but reference was made to AS1933A. This action, in essence, released aerospace elastomers from age control.

In the time since the cancellation of MIL-STD-1523A confusion has reigned. Contractors are not aware of the history of age control and still insist on it. Quality organizations are not only still insisting on age control but are now using AS1933A for seals or referring to MIL-HDBK-695C.

Some of the insistence for age control is due to the requirement that the latest revision of specifications must be used and if age control or cure date requirements are removed, there is no traceability to specification revisions. In addition, organizations are concerned about FIFO requirements being maintained.

3.4 ARP5316

To address the needs of contractors and to alleviate the confusion created by the cancellation of MIL-STD-1523A, ARP5316 was issued. This recommended practice addresses elastomeric seal components and offers a control document for those organizations which require one. It includes recommended shelf life limits that are consistent with the data from the cumulative studies on age control. It addresses the need for traceability and proper storage of elastomeric components of seals. It also provides a document that addresses seals not hoses, rubber boots, etc. It provides a reference source for Quality Organizations to work with.

The recommended storage times are based upon industry input regarding practical storage limits based upon FIFO requirements. Most users of the elastomers addressed in this ARP will find that the times listed in the document are beyond the time periods utilized in FIFO programs. More importantly, proper storage and traceability are emphasized since these are the key elements in promoting long shelf life and ensuring that the elastomeric seal components meet the latest revision of a specification.

3.5 MIL-HDBK-695D

This recently released revision directs the reader to ARP5316 for questions concerning elastomer seal shelf life.

3.6 DOD 4141.27.M

The DOD Shelf Life Management Manual uses ARP5316 as its key reference for elastomer seal shelf life.

4. PACKAGING

4.1 Unless otherwise specified by the customer at the time of order, the elastomeric seal or seal assembly shall be packaged:

- a. in individually sealed envelopes by the manufacturer, or
- b. in individually sealed packets in multiple envelopes by the manufacturer provided that individually packaged elastomeric seals or assemblies can be removed without affecting the seal integrity of the other packets.
- c. If the parts are repackaged by a distributor, the manufacturer will ship the properly identified parts to the distributor then the responsibility for the parts shifts to the distributor since the manufacturer cannot ensure that the parts will be properly packaged with minimum exposure to environmental conditions.

The packaging shall be carried out in an atmosphere in which the relative humidity is not greater than 65%. Contamination by oil, grease, etc., shall be avoided.

Seal assemblies (all components) shall be packaged in the same sealed envelope so that all elements of the assembly are present when the package is opened.

4.2 Packaging Materials

All packaging materials shall be free of copper naphthenates or creosote preservatives which can degrade rubber.

Suitable materials include Kraft bags and opaque polyethylene bags more than 0.075 mm thick. Opaque packaging is required. Metal foil bags can be used provided they are salt free.

NOTE: Phosphate ester hydraulic fluids and polyol ester based gas turbine lubricants soften and compromise polyethylene bags so care should be taken to avoid exposure of polyethylene storage bags to fluids.

4.3 Labeling

Each package or container shall be labeled with the following information which shall be visible from the outside of the package without breaking the seal:

- a. Manufacturers' part number;
- b. Specification number and Revision level;
- c. Customer's part number and/or contract number (if requested);
- d. Quantity in package;
- e. Manufacturer's name and/or identity number (such as CAGE Code);
- f. Quarter and Year of cure or manufacturer of the rubber component (e.g., July to September 1997 = 3Q97);
- g. Manufacturer's batch number;
- h. Rubber class designation per ASTM D1418;
- i. Packager's name (if different from manufacturer) and packaged date.

Expiration date will be added to the label for direct military procurement. It is not required to be on the label and will be added only when Purchaser specifically requests the addition because of direct military procurement.

AMS2817 allows individually packaged parts to be supplied to a distributor who can then allocate them to orders: If parts are purchased from the manufacturer under one contract number and sold, without being repackaged, by the supplier to the consumer under a different contract number, the original contract number shall be crossed out and the new contract number applied in the heat seal area of the envelope. Thus cradle to grave traceability and maximum protection of the elastomer seal element is guaranteed.

5. STORAGE

5.1 Temperature

The storage temperature shall be below 100 °F (38 °C), except when higher temperatures are caused by temporary climate changes, and articles shall be stored away from direct sources of heat such as boilers, radiators, and direct sunlight.

NOTE: If the storage temperature is below 59 °F (15 °C), care should be exercised during the handling of stored articles as they may have stiffened and become susceptible to distortion if not handled carefully.

The temperature of articles stored below 59 °F (15 °C) shall be raised to approximately 68 °F (20 °C) throughout their mass before being installed into a component.

5.2 Humidity

The relative humidity shall be such that given the variations of temperature in storage, condensation does not occur. In any event, if the elastomers are not stored in sealed moisture proof bags, the relative humidity of the atmosphere in storage shall be less than 75% r h, or if polyurethanes are being stored, shall be less than 65% r h.

5.3 Light

Elastomeric seals shall be protected from light sources, in particular direct sunlight or intense artificial light having an ultraviolet content. The individual opaque storage bags offer the best protection.

NOTE: It is advisable that windows of storage rooms where elastomers are stored in bulk be covered with a red or orange coating or screen.

5.4 Radiation

Precautions shall be taken to protect stored articles from all sources of ionizing radiation likely to cause damage to stored articles.

5.5 Ozone

As ozone is particularly deleterious to some elastomeric seals, storage rooms shall not contain any equipment that is capable of generating ozone such as mercury vapor lamps, high voltage electrical equipment giving rise to electric sparks or silent electrical discharges. Combustion gases and organic vapor shall be excluded from storage rooms as they may give rise to ozone via photochemical processes.

5.6 Deformation

Elastomeric seals shall be stored free from superimposed tensions and compressive stresses or other causes of deformation. Where articles are packaged in a strain-free condition, they shall be stored in their original packaging. In case of doubt, the manufacturer's advice shall be sought.

Rings of large inside diameter shall be formed into three equal superimposed loops so as to avoid creasing or twisting.

NOTE: It is not possible to achieve this condition by forming just two loops.

5.7 Contact with Liquid and Semi-Solid Materials

Elastomeric seals shall not be allowed to come into contact with liquid or semi-solid materials (for example, gasoline, greases, acids, disinfectants, cleaning fluids) or their vapors at any time during storage unless these materials are by design an integral part of the component or the manufacturer's packaging. When elastomeric seals are received coated with their operational media, they shall be stored in this condition.

5.8 Contact with Metals

Certain metals and their alloys (in particular, copper, manganese, and iron) are known to have deleterious effects on elastomers. Elastomeric seals shall not be stored in contact with such metals (except when bonded to them) but shall be protected by individual packaging.

5.9 Contact with Dusting Powder

Dusting powders shall only be used for the packaging of elastomeric items in order to prevent blocking. In such instances, the minimum quantity of powder to prevent adhesion shall be used.

5.10 Contact between Different Elastomers

Contact between different polymeric elastomers and elastomers of different seals shall be avoided. They shall not be packaged together in the same envelope.

5.11 Elastomeric Seals with Metal Parts Bonded to Them

The metal part of bonded elastomeric seals shall not come in contact with the elastomeric element of another seal. The bonded seal shall be individually packaged. Any preservative used on the metal shall be such that it will not affect the elastomeric element or the bond to such an extent that the seal will not comply with the product specification.

5.12 Stock Rotation

Elastomeric seal stock should be rotated on the FIFO principle (First In - First Out) so that the most recent manufactured parts remain in inventory.

6. RECORDING OF DATA DURING STORAGE

6.1 Recording

A record shall be kept of the initial physical properties and the dimensional characteristics of the elastomeric seal elements placed in storage. The records shall include the actual numerical results of the physical property tests for that batch of seals and the range of properties observed during testing. This record shall be maintained by the customer's Quality Organization until such time that the stock of seals has been depleted.

In addition to the inspection and testing reports, a record shall be maintained of the label information so that all information can be cross referenced.

7. DISCARDING OF SEALS

7.1 After Storage Life Has Been Exceeded

Once the storage life has expired, the elastomeric seals should be removed from inventory and destroyed per internal company procedures for the destruction of such materials.

8. STORAGE PERIOD

8.1 Duration of Storage

Unless otherwise specified in the product specification or Purchase Order notes, the maximum storage periods for unassembled elastomeric seal elements shall be those described in Tables 1, 2, and 3. This presupposes that the stored elastomers meet the current technical requirements. If they do not, they must be discarded since only those elastomeric seals that meet the current technical requirements should be used in applications to provide the highest integrity seal for the current system requirements.

The determination of the storage period is sometimes erroneously calculated. The correct procedure is based upon determining the first quarter of storage using the following procedure: Elastomeric items manufactured during any given quarter shall not be considered one quarter old until the end of the succeeding quarter. For example, a product cured during January, February or March of any year will not be considered one quarter old until July 1 of that same year. A product cured during October, November or December of any year will not be considered one quarter old until April 1 of the following year.

TABLE 1 - AEROSPACE MATERIAL SPECIFICATIONS

Specification	Title	Polymer	Maximum Storage Life (Years)
AMS3200	Butadiene-Acrylonitrile (NBR) Rubber Petroleum-Base Hydraulic Fluid Resistant (55-65)	NBR	15
AMS3201	Butadiene Acrylonitrile (NBR) Rubber, Dry Heat Resistant, 35-45	NBR	15
AMS3202	Butadiene-Acrylonitrile (NBR) Rubber Dry Heat Resistant (55-65)	NBR	15
AMS3205	Synthetic Rubber Low-Temperature Resistant, 45-55	CR	15
AMS3208	Chloroprene (CR) Rubber, Weather Resistant, 45-55	CR	15
AMS3209	Chloroprene Rubber, Weather Resistant (65-75)	CR	15
AMS3210	Chloroprene Rubber, Electrical Resistant (65-75)	CR	15
AMS3212	Acrylonitrile Butadiene (NBR) Rubber Aromatic Fuel Resistant (55-65)	NBR	15
AMS3213	Acrylonitrile Butadiene (NBR) Rubber Aromatic Fuel Resistant (75-85)	NBR	15
AMS3214	Acrylonitrile Butadiene (NBR) Rubber, Aromatic Fuel Resistant, 35-45	NBR	15
AMS3215	Acrylonitrile Butadiene (NBR) Rubber Aromatic Fuel Resistant (65-75)	NBR	15
AMS3216	Fluorocarbon (FKM) Rubber, High Temperature - Fluid Resistant Low Compression Set (70-80)	FKM	Unlimited
AMS3218	Fluorocarbon (FKM) Rubber, High Temperature - Fluid Resistant Low Compression Set (85-95)	FKM	Unlimited
AMS3220	Rubber, Synthetic General Purpose, Fluid Resistant, 55-65	NBR	15
AMS3227	Acrylonitrile Butadiene (NBR) Rubber, Hot Oil and Coolant Resistant, Low Swell (55-65)	NBR	15
AMS3228 (CANCELLED)	Acrylonitrile Butadiene (NBR) Rubber, Hot Oil and Coolant Resistant, Low Swell (65-75)	NBR	15
AMS3229 (NONCURRENT)	Acrylonitrile Butadiene (NBR) Rubber, Hot Oil and Coolant Resistant, Low Swell (75-85)	NBR	15
AMS3237	Butyl (IIR) Rubber, Phosphate Ester Resistant, 35-45	IIR	Unlimited
AMS3238	Butyl (IIR) Rubber, Phosphate Ester Resistant (65-75)	IIR	Unlimited
AMS3239	Butyl (IIR) Rubber, Phosphate Ester Resistant (85-95)	IIR	Unlimited
AMS3240	Chloroprene (CR) Rubber, Weather Resistant, 35-45	CR	15

TABLE 1 - AEROSPACE MATERIAL SPECIFICATIONS (CONTINUED)

Specification	Title	Polymer	Maximum Storage Life (Years)
AMS3241	Chloroprene (CR) Rubber Weather Resistant (55-65)	CR	15
AMS3242	Chloroprene (CR) Rubber Weather Resistant (75-85)	CR	15
AMS3243	Chloroprene (CR) Rubber Flame Resistant (55-65)	CR	15
AMS3244	Chloroprene (CR) Rubber Flame Resistant (65-75)	CR	15
AMS3248	Ethylene Propylene (EPM) Rubber Phosphate Ester Resistant 55-65	EPDM	Unlimited
AMS3249	Ethylene Propylene (EPDM) Rubber, Hydrazine-Base-Fluid Resistant, 75-85	EPDM	Unlimited
AMS3260	Rubber, Ethylene-Propylene-Diene EPDM Type	EPDM	Unlimited
AMS3301	Silicone Rubber, General Purpose, 40 Durometer	Q	Unlimited
AMS3302	Silicone Rubber, General Purpose (45-55)	Q	Unlimited
AMS3303	Silicone Rubber, General Purpose (55-65)	Q	Unlimited
AMS3304	Silicone Rubber, General Purpose (65-75)	Q	Unlimited
AMS3305	Silicone Rubber, General Purpose (75-85)	Q	Unlimited
AMS3306	Rubber, Silicone 1200 psi (8.27 MPa) High Modulus (55-65)	VMQ	Unlimited
AMS3307	Silicone (VMQ) Rubber, Low Compression Set Non-Oil Resistant (65-75)	VMQ	Unlimited
AMS3325	Fluorosilicone (FVMQ) Rubber, Fuel & Oil Resistant (55-65)	FVMQ	Unlimited
AMS3327	Fluorosilicone (FVMQ) Rubber, High Temperature Fuel & Oil Resistant (70-80)	FVMQ	Unlimited
AMS3328	Fluorosilicone (FVMQ) Rubber, Fuel and Oil Resistant (35-45)	FVMQ	Unlimited
AMS3329	Fluorosilicone (FVMQ) Rubber, Fuel and Oil Resistant, High Strength, 45-55	FVMQ	Unlimited
AMS3330	Fluorosilicone (FVMQ) Rubber, Fuel and Oil Resistant (45-55)	FVMQ	Unlimited
AMS3331	Fluorosilicone (FVMQ) Rubber, Fuel and Oil Resistant (65-75)	FVMQ	Unlimited
AMS3334	Silicone Rubber, Extreme Low Temperature Resistant, 35-45	PVMQ	Unlimited
AMS3336	Silicone (PVMQ) Rubber, Extreme Low Temperature - Resistant (55-65)	PVMQ	Unlimited
AMS3337	Silicone (PVMQ) Rubber, High & Extreme Low Temperature Resistant (65-75)	PVMQ	Unlimited
AMS3338	Silicone (PVMQ) Rubber, Extreme Low Temperature Resistant (75-85)	PVMQ	Unlimited

TABLE 1 - AEROSPACE MATERIAL SPECIFICATIONS (CONTINUED)

Specification	Title	Polymer	Maximum Storage Life (Years)
AMS3345	Silicone Rubber, 1000 psi (6.90 MPa) Tensile Strength, 45-55	Q	Unlimited
AMS3346	Silicone Rubber - 1000 psi (55-65)	Q	Unlimited
AMS3347	Silicone Rubber - 1200 psi, High Modulus (45-55)	Q	Unlimited
AMS3348	Silicone (VMQ) Rubber 1150 psi (7.93 MPa) Tensile Strength, High Resiliency 25-35	VMQ	Unlimited
AMS3349	Silicone (VMQ) Rubber, 1100 psi (7.58 MPa) Tensile Strength, High Resiliency, 65-75	VMQ	Unlimited
AMS3356	Silicone (VMQ) Rubber, Lubricating Oil and Compression Set Resistant, Electrical Grade (55-65)	VMQ	Unlimited
AMS3357	Rubber, Silicone (VMQ), Lubricating Oil and Compression Set Resistant, 65-75	VMQ	Unlimited
AMS3382	Tetrafluoroethylene/Propylene Rubber (FEP) Hydraulic Fluid and Synthetic Oil Resistant 70 to 80 and 85 to 95	FEP	Unlimited
AMS3384	Rubber, Fluorocarbon Elastomer (FKM), 70 to 80 Hardness, Low Temperature Sealing Tg -22 °F (-30 °C), For Elastomeric Shapes or Parts in Gas Turbine Engine Oil, Fuel and Hydraulic Systems.	FKM	Unlimited
AMS7255	Rings, Sealing, Tetrafluoroethylene/Propylene Rubber (FEP) Hydraulic Fluid and Synthetic Oil Resistance 70 to 80	FEP	Unlimited
AMS7256	Rings, Sealing, Tetrafluoroethylene/Propylene Rubber (FEP) Hydraulic Fluid and Synthetic Oil Resistance 85 to 95	FEP	Unlimited
AMS7257	Rings, Sealing, Perfluorocarbon (FFKM), Rubber, High-Temperature-Fluid Resistant (70-80)	FFKM	Unlimited
AMS7258	Rings, Sealing, Acrylonitrile Butadiene (NBR) Rubber Fuel Resistant, Low Shrinkage (65-75)	NBR	15
AMS7259	Rings, Sealing, Fluorocarbon (FKM) Rubber High-Temperature-Fluid Resistant, Very Low Compression Set (85-95)	FKM	Unlimited
AMS7260	Rings, Butadiene-Acrylonitrile (NBR) Rubber, Molded Fuel and Low Temperature Resistant 70-80	NBR	15
AMS7264	Rings, Sealing, Silicone Rubber, High Temperature Resistant, Low Compression Set, 65-75	Q	Unlimited
AMS7266	Rings, Sealing, Fluorosilicone Rubber, General Purpose, High Temperature, Fuel and Oil Resistant 65-75	FVMQ	Unlimited
AMS7267	Rings, Sealing, Silicone (VSI) Rubber Heat Resistant, Low Compression Set (70-80)	VSI	Unlimited
AMS7268	Rings, Sealing, Silicone Rubber, Low Compression Set, Non-Oil Resistant (65-75)	Q	Unlimited
AMS7269	Rings, Sealing, Silicone (PVMQ) Rubber, Low Outgassing, Space and Vacuum Service (45-55)	PVMQ	Unlimited

TABLE 1 - AEROSPACE MATERIAL SPECIFICATIONS (CONTINUED)

Specification	Title	Polymer	Maximum Storage Life (Years)
AMS7270	Rings, Sealing, Butadiene-Acrylonitrile (NBR) Rubber, Fuel Resistant (65-65)	NBR	15
AMS7271	Rings, Sealing, Butadiene-Acrylonitrile (NBR) Rubber Fuel and Low Temperature Resistant (60-70)	NBR	15
AMS7272	Rings, Sealing, Butadiene-Acrylonitrile (NBR) Rubber Synthetic Lubricant Resistant 67-75	NBR	15
AMS7273	Rings, Sealing, Fluorosilicone (FVMQ) Rubber, High Temperature Fuel and Oil Resistant 70-80	FVMQ	Unlimited
AMS7274	Rings, Sealing, Butadiene-Acrylonitrile (NBR) Rubber Oil Resistant (65-75)	NBR	15
AMS7276	Rings, Sealing Fluorocarbon (FKM) Rubber High-Temperature - Fluid Resistant Very-Low Compression Set (70-80)	FKM	Unlimited
AMS7287	Fluorocarbon Elastomer (FKM), High Temperature / HTS Oil Resistant/ Fuel Resistant Low Compression Set/ 70 to 80 Hardness, Low Temperature Tg -22 °F (-30 °C), For Seals in Oil/ Fuel/ Specific Hydraulic Systems.	FKM	Unlimited
AMS7379	Rubber: Fluorocarbon Elastomer (FKM) 70 to 80 Hardness, Low Temperature Sealing Tg -40 °F (-40 °C) For Elastomer Seals in Aircraft Engine Oil, Fuel and Hydraulic Systems	FKM	Unlimited
AMS-P-5315	Packing, Preformed, Hydrocarbon Fuel Resistant	NBR	15
AMS-P-5510	Packing, Preformed, Straight Thread Tube Fitting Boss, Type Hydraulic (-65° to 160°F)	NBR	15
AMS-P-5516 (SUPERSEDED BY MIL-DTL-5516)	Packing, Preformed, Petroleum Hydraulic Fluid Resistant, 160°F.	NBR	15
AMS-P-25732 (CANCELLED S/S by MIL-P-25732)	Packaging, Preformed, Petroleum Hydraulic Fluid Resistant, Limited Service at 275°F (135°C)	NBR	15
AMS-P-83461	Packing, Preformed, Petroleum Hydraulic Fluid Resistant, Improved Performance at 275°F (135°C)	NBR	15
AMS-R-6855	Rubber, Synthetic, Sheets, Strips, Molded or Extruded Shapes		
	Class 1 - All Grades	NBR	15
	Class 2 - All Grades	CR	15
	Class 3 - All Grades	SBR	3
	Class 4 - All Grades	CR	15
	Class 5 - All Grades	SBR	3
AMS-R-7362	Rubber, Synthetic, Solid, Sheet, Strip and Fabricated Parts, Synthetic Oil Resistant	NBR	15
AMS-R-25988	Rubber, Fluorosilicone Elastomer, Oil and Fuel Resistant, Sheets, Strips, Molded Parts and Extruded Shapes	FVMQ	Unlimited
AMS-R-83248 (CANCELLED S/S by AMS3216, 3218, 7259, 7276)	Rubber, Fluorocarbon Elastomer, High Temperature, Fluid, and Compression Set Resistant	FKM	Unlimited

TABLE 1 - AEROSPACE MATERIAL SPECIFICATIONS (CONTINUED)

Specification	Title	Polymer	Maximum Storage Life (Years)
AMS-R-83285	Rubber, Ethylene-Propylene, General Purpose	EPDM	Unlimited
AMS-R-83412	Rubber, Ethylene-Propylene, Hydrazine Resistant	EPDM	Unlimited
AMS-R-83485	Rubber, Fluorocarbon Elastomer, Improved Performance at Low Temperature	FKM	Unlimited
NAS1613	Seal Element, Packing, Preformed, Ethylene Propylene Rubber	EPDM	Unlimited

NOTE: Some organizations consider "Unlimited" as the equivalent of 25 years.

SAENORM.COM : Click to view the full PDF of arp5316d

TABLE 2 - MILITARY AND FEDERAL SPECIFICATIONS

Specification	Title	Polymer	Maximum Storage Life (Years)
MIL-DTL-432 (INACTIVE)	Gaskets, Nonmetallic, Synthetic Rubber	NBR	15
MIL- DTL-81716 (INACTIVE)	Packing, Preformed, Straight Thread Tube Fitting Boss, Type II Hydraulic (Minus 65°F to Plus 275°)	NBR	15
MIL- DTL-83397 (INACTIVE)	Rubber, Polyurethane, Castable, Humidity Resistant	AU or EU	5
MIL-P-5315 (CANCELLED S/S by AMS-P-5315)	Packing, preformed, hydrocarbon fuel resistant	NBR	15
MIL-P-5510 (CANCELLED S/S by AMS-P-5510)	Packing, preformed, straight tube fitting boss, type 1 hydraulic (-65 deg to 160 deg F)	NBR	15
MIL-P-5516 (REVISED TO MIL-DTL-5516 AND INACTIVE)	Packing, preformed, petroleum hydraulic fluid resistant, 160 deg F	NBR	15
MIL-P-25732 (INACTIVE)	Packing, preformed, petroleum hydraulic fluid	NBR	15
MIL- PRF-2765	Rubber Sheet, Strip, Extruded, & Molded Shapes, Synthetic, Oil Resistant	NBR	15
MIL- PRF-6855	Rubber, Synthetic, Sheets, Strips, Molded or Extruded Shapes Class 1 - All Grades Class 2 - All Grades Class 3 - All Grades Class 4 - All Grades Class 5 - All Grades	NBR CR SBR CR SBR	15 15 3 15 3
MIL-R-7362 (CANCELLED S/S by AMS-R-7362)	Rubber, synthetic, solid, sheet, strip and fabricated parts, synthetic oil resistant	NBR	15
MIL- DTL-25988	Rubber, fluorosilicone elastomer, oil-and-fuel-resistant, sheets, strips, molded & extruded	FVMQ	Unlimited
MIL-R-81828 (CANCELLED)	Rubber, Chlorosulfonated Polyethylene Elastomer, Sheet & Molded Shapes, Ozone Resistant	CSM	15
MIL-R-83248 (CANCELLED S/S by AMS3216, 3218, 7259, 7272)	Rubber, Fluorocarbon Elastomer, High Temperature, Fluid and Compression Set Resistant	FKM	Unlimited
MIL-R-83285 (CANCELLED S/S by AMS-R-83285)	Rubber, Ethylene-Propylene, General Purpose	EPDM	Unlimited
MIL-R-83412 (CANCELLED S/S by AMS-R-83412)	Rubber, Ethylene-propylene, Hydrazine Resistant	EPDM	Unlimited