



SAE Executive Standards Committee Rules provide that: " This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

REV. A	FEDERAL SUPPLY CLASS		RATIONALE		
			THIS TECHNICAL REPORT IS BEING STABILIZED BECAUSE IT COVERS TECHNOLOGY, PRODUCTS, OR PROCESSES WHICH ARE MATURE AND NOT LIKELY TO CHANGE IN THE FORESEEABLE FUTURE.		
AS1298™	STABILIZED NOTICE		THIS DOCUMENT HAS BEEN DECLARED "STABILIZED" BY SAE G-3, AEROSPACE COUPLINGS, FITTINGS, HOSE, TUBING ASSEMBLIES COMMITTEE AND WILL NO LONGER BE SUBJECTED TO PERIODIC REVIEWS FOR CURRENCY. USERS ARE RESPONSIBLE FOR VERIFYING REFERENCES AND CONTINUED SUITABILITY OF TECHNICAL REQUIREMENTS. NEWER TECHNOLOGY MAY EXIST.		
SAENORM.COM : Click to view the full PDF of as1298a			For more information on this standard, visit https://www.sae.org/standards/content/AS1298A/ THIRD ANGLE PROJECTION 		
			CUSTODIAN: G-3 PROCUREMENT SPECIFICATION:		
		AEROSPACE STANDARD		AS1298™	REV. A
SLEEVE, HEAVY WALL, HOSE ASSEMBLY, CHAFE GUARD, TFE					



Size	D Inside Diameter						T Wall Thickness						Weight	
	Nominal		Maximum		Minimum		Nominal		Maximum		Minimum			
	in.	mm	in.	mm	in.	mm	in.	mm	in.	mm	in.	mm	lbs/ft	kgs/m
-1	.320	8.13	.330	8.38	.310	7.87	.035	.89	.045	1.14	.025	.64	.041	.061
-2	.375	9.53	.385	9.78	.365	9.27	.035	.89	.045	1.14	.025	.64	.044	.065
-3	.450	11.43	.460	11.68	.440	11.18	.035	.89	.045	1.14	.025	.64	.048	.071
-4	.540	13.72	.550	13.97	.530	13.46	.040	1.02	.050	1.27	.030	.76	.067	.099
-5	.635	16.13	.645	16.38	.625	15.87	.040	1.02	.050	1.27	.030	.76	.083	.123
-6	.730	18.54	.740	18.80	.720	18.29	.040	1.02	.050	1.27	.030	.76	.093	.138
-7	.865	21.97	.875	22.23	.855	21.72	.045	1.14	.055	1.40	.035	.89	.118	.175
-8	1.090	27.69	1.100	27.94	1.080	27.43	.050	1.27	.060	1.52	.040	1.02	.150	.223
-9	1.130	28.70	1.140	28.96	1.120	28.45	.050	1.27	.060	1.52	.040	1.02	.153	.227
-10	1.195	30.35	1.205	30.61	1.185	30.10	.050	1.27	.060	1.52	.040	1.02	.168	.249
-11	1.375	34.93	1.385	35.18	1.365	34.67	.055	1.40	.065	1.65	.045	1.14	.232	.345
-12	1.440	36.58	1.450	36.83	1.430	36.32	.055	1.40	.065	1.65	.045	1.14	.242	.360
-13	1.770	44.96	1.780	45.21	1.760	44.70	.060	1.52	.070	1.78	.050	1.27	.370	.550
-14	2.065	52.45	2.075	52.71	2.055	52.20	.060	1.52	.070	1.78	.050	1.27	.390	.580

NOTES:

1. USAGE: USED AS AN OUTER PROTECTIVE COVER ON HOSE AND/OR HOSE ASSEMBLIES TO INHIBIT THE DETRIMENTAL EFFECTS OF ABRASION AND OTHER ENVIRONMENTAL CONDITIONS, THEREBY INCREASING SERVICE LIFE.
2. MATERIAL: BLACK, EXTRUDED, SEAMLESS POLYTETRAFLUOROETHYLENE (TFE) TUBING.
3. RESISTANCE: SLEEVE SHALL HAVE EXCELLENT ABRASION RESISTANCE AND SHALL BE UNAFFECTED BY MOISTURE, OZONE, OXIDATION, HYDRAULIC FLUIDS, FUELS, SOLVENTS, AND MOST OTHER CHEMICALS AND FLUIDS USED IN AIRCRAFT APPLICATIONS.
4. PHYSICAL PROPERTIES: HIGH TENSILE STRENGTH AND AN ABILITY TO RETAIN USEFUL FLEXIBILITY, MECHANICAL STRENGTH, AND ELONGATION OVER A LARGE TEMPERATURE RANGE SHALL CHARACTERIZE THIS SLEEVE.