

Aluminum Alloy Tempers

1. SCOPE:

The purpose of this SAE Aerospace Standard (AS) is to provide a description of the temper nomenclature system for aluminum alloys used in the aerospace industry by combining information from different sources for the benefit of the user.

2. REFERENCES:

For further information on the tempers described in this document see:

ASTM E 29 Using Significant Digits in Test Data to Determine Conformance With Specification

ANSI H35.1/H35.1M American National Standard Alloy and Temper Designation Systems for Aluminum

Tempers for Aluminum and Aluminum Alloys Products - Published by The Aluminum Association, Inc.

Aluminum Standards and Data - Published by The Aluminum Association, Inc.

3. GENERAL:

The tempers used with aluminum alloys as registered with The Aluminum Association provide information regarding the basic operations used for making the property levels for the alloy and temper registered for the product.

This document provides information as to the general rules used by The Aluminum Association for describing the alloy-temper system (see Section 4). This section is an extraction from ANSI H35.1/H35.1M. This document also provides a list of alloy and tempers used in aerospace applications. The product form and the basic operations that determine the temper are shown (see Section 5). However, some of these alloy temper combinations are not currently used and may not be readily available.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1999 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-8510
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

SAE AS1990 Revision B

4. GENERAL RULES DESCRIBING THE ALUMINUM, ALUMINUM ALLOY-TEMPER SYSTEM:

The rules upon which this system is based are established by and can only be modified by ANSI Committee H35.

4.1 Temper Designation System:

The temper designation system is used for all forms of wrought and cast aluminum and aluminum alloys except ingot. It is based on the sequences of basic treatments used to produce the various tempers. The temper designation follows the alloy designation, the two being separated by a hyphen. Basic temper designations consist of letters. Subdivisions of the basic tempers, where required, are indicated by one or more digits following the letter. These designate specific sequences of basic treatments, but only operations recognized as significantly influencing the characteristics of the product are indicated. Should some other variation of the same sequence of basic operations be applied to the same alloy, resulting in different characteristics, then additional digits are added to the designation.

4.1.1 Basic Temper Designations: Basic temper designations are as follows:

- F As fabricated. Applies to the products of shaping processes in which no special control over thermal conditions or strain-hardening is employed. For wrought products, there are no mechanical property limits.
- O Annealed. Applies to wrought products that are annealed to obtain the lowest strength temper, and to cast products that are annealed to improve ductility and dimensional stability. The O may be followed by a digit other than zero.
- H Strain-hardened (wrought products only). Applies to products that have their strength increased by strain-hardening, with or without supplementary thermal treatments to produce some reduction in strength. The H is always followed by two or more digits.
- W Solution heat-treated. An unstable temper applicable only to alloys that spontaneously age at room temperature after solution heat-treatment. This designation is specific only when the period of natural aging is indicated; for example: W 1/2 h.
- T Thermally treated to produce stable tempers other than F, O, or H. Applies to products that are thermally treated, with or without supplementary strain-hardening, to produce stable tempers. The T is always followed by one or more digits.

SAE AS1990 Revision B

4.2 Subdivisions of Basic Tempers:

4.2.1 Subdivision of H Temper: Strain-Hardened:

4.2.1.1 The first digit following the H indicates the specific combination of basic operations, as follows:

- H1 Strain-hardened only. Applies to products that are strain-hardened to obtain the desired strength without supplementary thermal treatment. The number following this designation indicates the degree of strain-hardening.
- H2 Strain-hardened and partially annealed. Applies to products that are strain-hardened more than the desired final amount and then reduced in strength to the desired level by partial annealing. For alloys that age-soften at room temperature, the H2 tempers have the same minimum ultimate tensile strength as the corresponding H3 tempers. For other alloys, the H2 tempers have the same minimum ultimate tensile strength as the corresponding H1 tempers and slightly higher elongation. The number following this designation indicates the degree of strain-hardening remaining after the product has been partially annealed.
- H3 Strain-hardened and stabilized. Applies to products that are strain-hardened and whose mechanical properties are stabilized either by a low temperature thermal treatment or as a result of heat introduced during fabrication. Stabilization usually improves ductility. This designation is applicable only to those alloys which, unless stabilized, gradually age-soften at room temperature. The number following this designation indicates the degree of strain-hardening remaining after the stabilization treatment.

4.2.1.2 The digit following the designations H1X, H2X, and H3X indicates the degree of strain-hardening. Numeral 8 has been assigned to indicate tempers having an ultimate tensile strength equivalent to that achieved by a cold reduction [temperature during reduction not to exceed 122 °F (50 °C)] of approximately 75% following a full anneal. Tempers between O (annealed) and 8 are designated by numerals 1 through 7. Material having an ultimate tensile strength about midway between that of the O temper and that of the 8 temper is designated by the numeral 4; about midway between the O and 4 tempers by the numeral 2; and about midway between the 4 and 8 tempers by the numeral 6. Numeral 9 designates tempers whose minimum ultimate tensile strength exceeds that of the 8 temper by 2.0 ksi (14 MPa) or more. For two-digit H tempers with an odd second digit, the standard limits for strength are the arithmetic mean, rounded to the nearest multiple of 1.0 ksi (5 MPa) in conformance with ASTM E 29, of the standard limits for the adjacent two-digit H tempers with an even second digit.

SAE AS1990 Revision B

- 4.2.1.2.1 For alloys that cannot be cold reduced 75% after full anneal to establish an ultimate tensile strength applicable to the HX8 temper, the HX6 temper tensile strength may be established by a cold reduction of approximately 55% following a full anneal, or the HX4 temper tensile strength may be established by a cold reduction of approximately 35% after a full anneal.
- 4.2.1.3 The third digit¹, when used, indicates a variation of a two-digit temper. It is used when the degree of control of temper or the mechanical properties, or both, differ from, but are close to, that (or those) for the two-digit H temper designation to which it is added, or when some other characteristic is significantly affected. (See Annex for assigned three-digit H tempers.)
- 4.2.1.3.1 The minimum ultimate tensile strength of a three-digit H temper must be at least as close to that of the corresponding two-digit H temper as it is to the adjacent two-digit H tempers. Products in the H temper with mechanical properties below H_1 shall be variations of H_1.
- 4.2.2 Subdivision of T Temper: Thermally Treated:
- 4.2.2.1 Numerals 1 through 10 following the T indicate specific sequences of basic treatments, as follows²:
- T1 Cooled from an elevated temperature shaping process and naturally aged to a substantially stable condition. Applies to products that are not cold worked after cooling from an elevated temperature shaping process, or in which the effect of cold work in flattening or straightening may not be recognized in mechanical property limits.
 - T2 Cooled from an elevated temperature shaping process, cold worked, and naturally aged to a substantially stable condition. Applies to products that are cold worked to improve strength after cooling from an elevated temperature shaping process, or in which the effect of cold work in flattening or straightening is recognized in mechanical property limits.

1. Numerals 1 through 9 may be arbitrarily assigned as the third digit and registered with The Aluminum Association for an alloy and product to indicate a variation of a two-digit H temper.

2. A period of natural aging at room temperature may occur between or after the operations listed for the T tempers. Control of this period is exercised when it is metallurgically important.

SAE AS1990 Revision B

4.2.2.1 (Continued):

- T3 Solution heat-treated³, cold worked, and naturally aged to a substantially stable condition. Applies to products that are cold worked to improve strength after solution heat-treatment, or in which the effect of cold work in flattening or straightening is recognized in mechanical property limits.
- T4 Solution heat-treated³ and naturally aged to a substantially stable condition. Applies to products that are not cold worked after solution heat-treatment, or in which the effect of cold work in flattening or straightening may not be recognized in mechanical property limits.
- T5 Cooled from an elevated temperature shaping process and then artificially aged. Applies to products that are not cold worked after cooling from an elevated temperature shaping process, or in which the effect of cold work in flattening or straightening may not be recognized in mechanical property limits.
- T6 Solution heat-treated³ and then artificially aged. Applies to products that are not cold worked after solution heat-treatment, or in which the effect of cold work in flattening or straightening may not be recognized in mechanical property limits.
- T7 Solution heat-treated³ and overaged/stabilized. Applies to wrought products that are artificially aged after solution heat-treatment to carry them beyond a point of maximum strength to provide control of some significant characteristic.⁴ Applies to cast products that are artificially aged after solution heat-treatment to provide dimensional and strength stability.
- T8 Solution heat-treated³, cold worked, and then artificially aged. Applies to products that are cold worked to improve strength, or in which the effect of cold work in flattening or straightening is recognized in mechanical property limits.
- T9 Solution heat-treated³, artificially aged, and then cold worked. Applies to products that are cold worked to improve strength.
- T10 Cooled from an elevated temperature shaping process, cold worked, and then artificially aged. Applies to products that are cold worked to improve strength, or in which the effect of cold work in flattening or straightening is recognized in mechanical property limits.

3. Solution heat-treatment is achieved by heating cast or wrought products to a suitable temperature, holding at that temperature long enough to allow constituents to enter into solid solution and cooling rapidly enough to hold the constituents in solution. Some 6000 series alloys attain the same specified mechanical properties whether furnace solution heat treated or cooled from an elevated temperature shaping process at a rate rapid enough to hold constituents in solution. In such cases the temper designations T3, T4, T6, T7, T8, and T9 are used to apply to either process and are appropriate designations.

4. For this purpose, characteristic is something other than mechanical properties. The test method and limit used to evaluate material for this characteristic are specified at the time of the temper registration.

SAE AS1990 Revision B

4.2.2.2 Additional digits⁵, the first of which shall not be zero, may be added to designations T1 through T10 to indicate a variation in treatment that significantly alters the characteristics of the product. (See Annex for specific additional digits for T tempers.)

4.3 Variations of O Temper: Annealed:

4.3.1 A digit following the O, when used, indicates a product in the annealed condition having special characteristics. As the O temper is not part of the strain-hardened (H) series, variations of O temper shall not apply to products that are strain-hardened after annealing and in which the effect of strain-hardening is recognized in the mechanical properties or other characteristics.

5. LIST OF ALLOY-TEMPERS OF INTEREST TO THE AEROSPACE INDUSTRY:

5.1 General:

The following listing provides information as to the metallurgical process a particular alloy and temper receives beginning with solution heat treatment. The list is not intended to be a description of the registration or of the application for which the alloy-temper was designed. This information can be obtained through The Aluminum Association or an interested supplier.

5. Additional digits may be arbitrarily assigned and registered with The Aluminum Association for an alloy and product to indicate a variation of tempers T1 through T10 (see footnote 1). Variations in treatment that do not alter the characteristics of the product are considered alternate treatments for which additional digits are not assigned.

SAE AS1990 Revision B

5.2 Castings:

Process codes are as presented in Table 1.

- AA - Artificial age
- SHT - Solution heat treat
- NA - Natural age
- AO - Overaged
- M - Indicates the primary process variable modified to develop the characteristics associated with the temper variation. The significance of the numbers contained in the temper designation is not defined beyond what is shown in Section 4.

TABLE 1 - Process Codes

Alloy-Temper		Process Used to Obtain Temper
201.0	T4	SHT-NA
A201.0	T7	SHT-AO
A205.0	T7	SHT-AO
206.0	T4	SHT-NA
	T7	SHT-AO
	T4	SHT-NA
	T71	SHT-AO _M
222.0	T4	SHT-NA
	T61	SHT-AA
242.0	F	As Cast
	T4	SHT-NA
	T571	F Temper and AA
	T61	SHT (quench by air blast) - AA
243.0	T41	SHT-NA
	T61	SHT-AA
295.0	T4	SHT-NA
	T62	SHT-AA
296.0	T4	SHT-NA
	T6	SHT-AA
319.0	T4	SHT-NA
	T6	SHT-AA
354.0	T41	SHT-NA
	T61	SHT-AA

SAE AS1990 Revision B

TABLE 1 (Continued)

Alloy-Temper		Process Used to Obtain Temper
355.0	T4	SHT-NA
	T51	F-AA
	T6	SHT-AA
	T71	SHT-AO
C355.0	T4	SHT-NA
	T6	SHT-AA
	T61	SHT-AA _M
	T71	SHT-AO
356.0	F	As Cast
	T51	F-AA
	T6	SHT-AA
A356.0	T4	SHT-NA
	T6	SHT-AA
	T61	SHT-AA _M
	T51	F-AA
357.0	T4	SHT-NA
	T6	SHT-AA
	T61	SHT-AA _M
A357.0	T6	SHT-AA
358.0	T4	SHT-NA
	T6	SHT-AA
	T60	SHT-Controlled delay - AA
359.0	T4	SHT-NA
	T61	SHT-AA
	T62	SHT-AA (less than for T61)
520.0	T4	SHT-(Controlled cool in hot H ₂ O or oil)
712.0	F	As Cast
	T1	SHT (Cooled from Casting) - NA
	T5	T1-AA
850.0	F	As Cast
	T5	F-AA

5.3 Wrought Alloys:

(See codes at the end of Table 2):

TABLE 2 - Processes to Obtain Temper

Alloy-Temper	Product Form S	Product Form P	Product Form TD	Product Form TE	Product Form E	Product Form RCF	Product Form BCF	Product Form WCF	Product Form R	Product Form F _H	Product Form F _D	Product Form RR	Product Form F	Process Used to Obtain Temper
1100 - H12			x											CW approximately 1/4 hard
H14	x	x	x			x		x	x					CW approximately 1/2 hard
H16			x											CW approximately 3/4 hard
H18	x		x					x						CW approximately full hard
2004 - T6	x													SHT-AA
2011 - T3			x			x	x	x						SHT-CW-NA
T4						x	x							SHT-NA
T451						x	x							SHT-SR _S -NA
T4511			x			x								SHT-SR _S -NA (Minor straightening after SR _S allowed)
T8			x			x	x	x						SHT-CW-AA
T6						x	x	x						SHT-AA
T651						x	x	x						SHT-SR _S -AA
2014 - T3	x													SHT-CW-NA
T4	x		x	x	x	x	x	x			x			SHT-NA
T42	x	x	x	x	x	x	x	x						Not available from producer - see A.2.2
T451		x				x	x							SHT-SR _S -NA
T4510				x	x									SHT-SR _S -NA
T4511				x	x									SHT-SR _S -NA (Minor straightening after SR _S allowed)
T6	x		x	x	x	x	x	x		x	x	x		SHT-AA
T61										x	x			SHT (Quenched in boiling water) - AA
T62	x	x	x	x	x	x	x	x						Not available from producer - see A.2.2
T611										x	x			SHT (Quenched in hot water) - AA
T651		x				x	x							SHT-SR _S -AA
T652										x		x		SHT-SR _C -AA
T6510				x	x									SHT-SR _S -AA
T6511			x	x	x									SHT-SR _S -AA (Minor straightening after SR _S allowed)

SAE AS1990 Revision B

TABLE 2 - Processes to Obtain Temper (Continued)

Alloy-Temper	Product Form S	Product Form P	Product Form TD	Product Form TE	Product Form E	Product Form RCF	Product Form BCF	Product Form WCF	Product Form R	Product Form F _H	Product Form F _D	Product Form RR	Product Form F	Process Used to Obtain Temper
2017 - H13						X		X						CW approximately 1/4 to 1/2 hard
H15								X						CW approximately 1/2 hard
T4						X	X	X	X					SHT-NA
T42						X	X	X						Not available from producer - see A.2.2
T451						X	X	X						SHT-SR _S -NA
2018 - T61											X			SHT (Quenched in boiling water) - AA
T71											X			SHT (Quenched in boiling water) - AO
2024 - H13						X		X						CW approximately 1/4 to 1/2 hard
H23								X						CW - partial anneal
T3	X		X	X	X	X	X	X					X	SHT-CW-NA
T351		X				X	X							SHT-SR _S -NA
T3510				X	X									SHT-SR _S -NA
T3511			X	X	X									SHT-SR _S -NA (Minor straightening after SR _S allowed)
T36								X						SHT-CW (Approximately 6%) - NA
T361	X	X												SHT-CW (Approximately 6%) - NA
T37			X											SHT-CW (Approximately 8%) - NA
T4	X					X	X	X	X					SHT-NA
T42	X	X	X	X	X	X	X	X	X					Not available from producer - see A.2.2
T6						X	X	X						SHT-AA
T62	X	X				X	X	X						Not available from producer - see A.2.2
T81			X										X	SHT-CW-AA
T84			X											SHT-CW (Approximately 4%) - AA
T851		X				X		X						SHT-SR _S -AA
T8510				X	X									SHT-SR _S -AA
T8511			X	X	X									SHT-SR _S -AA (Minor straightening after SR _S allowed)
T861	X	X												SHT-CW (Approximately 6%) - AA
2025 - T6											X	X		SHT-AA
2048 - T851		X												SHT-SR _S -AA
2117 - H13					X			X						CW approximately 1/4 to 1/2 hard
H15					X			X						CW approximately 1/2 to 3/4 hard
T4									X					SHT-NA

SAE AS1990 Revision B

TABLE 2 - Processes to Obtain Temper (Continued)

Alloy-Temper	Product Form S	Product Form P	Product Form TD	Product Form TE	Product Form E	Product Form RCF	Product Form BCF	Product Form WCF	Product Form R	Product Form F _H	Product Form F _D	Product Form RR	Product Form F	Process Used to Obtain Temper
2124 - T351		x												SHT-SR _S -NA
T851		x												SHT-SR _S -AA
2218 - T61											x			SHT (Quenched in boiling water) - AA
T71											x			SHT (Quenched in boiling water) - AO
2219 - T31	x		x	x	x									SHT-CW-NA
T351		x										x		SHT-SR _S -NA
T3510				x	x									SHT-SR _S -NA
T3511				x	x									SHT-SR _S -NA (Minor CW after SR _S allowed)
T37	x	x												SHT-CW (Approximately 8%) - NA
T6									x	x	x	x		SHT-AA
T62	x	x		x	x									Not available from producer - see A.2.2
T71										x	x			SHT (Quenched in boiling water) - AO
T81	x		x	x	x									SHT-CW-AA
T851		x				x						x		SHT-SR _S -AA
T8510				x	x			x						SHT-SR _S -AA
T8511				x	x									SHT-SR _S -AA (Minor straightening after SR _S allowed)
T852			x		x					x	x	x		SHT-SR _C -AA
T87	x	x												SHT-CW (Approximately 8%) - AA
2224 - T3510					x									SHT-SR _S -NA
T3511					x									SHT-SR _S -NA (Minor straightening after stretch allowed)
2324 - T39		x												SHT-CW (Approximately 11%) - SR _S
2519 - T87		x												SHT-CW-AA
2618 - T61										x	x			SHT (Quenched in boiling water) - AA
T71										x	x			SHT (Quenched in boiling water) - AO
3003 - H14	x	x	x			x		x	x					Cold worked approximately 1/2 hard
H142			x											CW (approximately 29%) M
H16			x											CW (approximately 3/4 hard)
H18	x		x					x						Cold worked approximately full hard

SAE AS1990 Revision B

TABLE 2 - Processes to Obtain Temper (Continued)

Alloy-Temper	Product Form S	Product Form P	Product Form TD	Product Form TE	Product Form E	Product Form RCF	Product Form BCF	Product Form WCF	Product Form R	Product Form F _H	Product Form F _D	Product Form RR	Product Form F	Process Used to Obtain Temper
3003 - Continued														
H183			x											CW (approximately 74%) M
H281			x											CW (approximately full hard) M - PA
4032 - T6											x			SHT-AA
T65					x									SHT-SR _S -AA
T86					x			x						SHT-CW-AA
5052 - H32	x	x	x			x		x	x					Cold worked approximately 1/4 hard - stabilized
H34	x	x	x					x						Cold worked approximately 1/2 hard - stabilized
H36			x											CW (approximately 3/4 hard) - stabilized
H191													x	Cold worked more than H18 temper
5056 - H191													x	Cold worked more than H18 temper
5083 - H111				x	x					x	x			Some CW introduced after an anneal
H112				x	x					x	x			Some strain hardening when working at an elevated temp.
H321	x	x												CW approximately 1/4 hard - stabilized
H323	x													CW approximately 1/4 hard - stabilized
H343	x													CW approximately 1/2 hard - stabilized
5086 - H32	x	x												CW approximately 1/4 hard - stabilized
H34	x	x												CW approximately 1/2 hard - stabilized
H111					x									Some CW introduced after an anneal
H112					x									Some strain hardening when working at an elevated temp.
5454 - H32	x	x												CW approximately 1/4 hard - stabilized
H34	x	x												CW approximately 1/2 hard - stabilized
H111					x									Some CW introduced after an anneal
H112					x									Some strain hardening when working at an elevated temp.
5456 - H112	x	x			x									Some strain hardening when working at an elevated temp.
H321	x	x												CW approximately 1/4 hard - stabilized
H111					x									Some CW introduced after an anneal
H112					x									Some strain hardening when working at an elevated temp.

SAE AS1990 Revision B

TABLE 2 - Processes to Obtain Temper (Continued)

Alloy-Temper	Product Form S	Product Form P	Product Form TD	Product Form TE	Product Form E	Product Form RCF	Product Form BCF	Product Form WCF	Product Form R	Product Form F _H	Product Form F _D	Product Form RR	Product Form F	Process Used to Obtain Temper
6013 - T4	x													SHT-NA
T42	x													Not available from producer - see A.2.2
T6	x													SHT-AA
T62	x													Not available from producer - see A.2.2
6061 - H13														Cold worked approximately 1/4 to 1/2 hard
T4	x		x	x			x	x						SHT-NA
T42	x	x	x	x			x	x						Not available from producer - see A.2.2
T451		x					x							SHT-SR _S -NA
T4510			x	x										SHT-SR _S
T4511			x	x										SHT-SR _S -NA (Minor straightening after SR _S allowed)
T6	x		x	x			x	x	x	x	x	x		SHT-AA
T62	x	x	x	x			x	x						Not available from producer - see A.2.2
T651		x		x			x							SHT-SR _S -AA
T652										x				SHT-SR _C -AA
T6510			x	x								x		SHT-SR _S -AA
T6511			x	x										SHT-SR _S -AA (Minor straightening after SR _S allowed)
T81			x											SHT-CW _M -AA
T89								x						SHT-CW _M -AA
T913								x						SHT-AA _M -CW
T94								x						SHT-AA _M -CW
6063 - T4			x	x										SHT-NA
T42			x	x										Not available from producer - see A.2.2
T6			x	x										SHT-AA
T62			x	x										Not available from producer - see A.2.2
T83			x											SHT-CW _M -AA
T831			x											SHT-CW _M -AA
T832			x											SHT-CW _M -AA
T837			x											SHT-CW _M -AA

SAE AS1990 Revision B

TABLE 2 - Processes to Obtain Temper (Continued)

Alloy-Temper	Product Form S	Product Form P	Product Form TD	Product Form TE	Product Form E	Product Form RCF	Product Form BCF	Product Form WCF	Product Form R	Product Form F _H	Product Form F _D	Product Form RR	Product Form F	Process Used to Obtain Temper
6066 - T4			x	x	x									SHT-NA
T42			x	x	x									Not available from producer - see A.2.2
T4510				x	x									SHT-SR _S -NA
T4511				x	x									SHT-SR _S -NA (Minor straightening after SR _S allowed)
T6			x	x	x						x			SHT-AA
T62			x	x	x									Not available from producer - see A.2.2
T6510				x	x									SHT-SR _S -AA
T6511				x	x									SHT-SR _S -AA (Minor straightening after SR _S allowed)
6151 - T6											x	x		SHT-AA
6951 - T6	x				x									SHT-AA
7001 - T6				x	x									SHT-AA
T62				x	x									Not available from producer - see A.2.2
T6510				x	x									SHT-SR _S -AA
T6511				x	x									SHT-SR _S -AA (Minor straightening after SR _S allowed)
7010 - T7351	x													SHT-SR _S -AO (More than - T73651 temper)
T7451	x													SHT-SR _S -AO (More than - T7651 temper)
T7651	x													SHT-SR _S -AO
7049 - T73										x	x			SHT-AO
T7351	x													SHT-SR _S -AO
T7352									x					SHT-SR _C -AO
T73511				x	x									SHT-SR _S -AO (Minor straightening after SR _S allowed)
*T74											x			SHT-AO (Less than for T73 temper)
T76511				x	x									SHT-SR _S -AO (Minor straightening after SR _S allowed)
7050 - H13						x		x						Cold worked approximately 1/4 to 1/2 hard
T7									x					SHT-SR _S -AO
T73									x					SHT-SR _S -AO
T73510					x									SHT-SR _S -AO
T73511				x	x									SHT-SR _S -AO (Minor straightening after SR _S allowed)
*T74										x	x			SHT-AO

SAE AS1990 Revision B

TABLE 2 - Processes to Obtain Temper (Continued)

Alloy-Temper	Product Form S	Product Form P	Product Form TD	Product Form TE	Product Form E	Product Form RCF	Product Form BCF	Product Form WCF	Product Form R	Product Form F _H	Product Form F _D	Product Form RR	Product Form F	Process Used to Obtain Temper
7050 - Continued														
*T7451		x										x		SHT-SR _S -AO
*T74510					x									SHT-SR _S -AO
*T74511			x											SHT-SR _S -AO (Minor straightening after SR _S allowed)
*T7452										x	x	x		SHT-SR _C -AO
*T7454											x			SHT-SR _(S&C) -AO
T76	x		x											SHT-AO
T7651		x												SHT-SR _S -AO
T76510					x									SHT-SR _S -AO
T76511			x		x									SHT-SR _S -AO (Minor straightening after SR _S allowed)
7055 - T7751		x												SHT-SR _S -AO
7075 - H13						x		x						Cold worked approximately 1/4 to 1/2 hard
T6	x		x		x	x	x	x	x	x	x	x		SHT-AA
T62	x	x	x		x	x	x	x						Not available from producer - see A.2.2
T651		x				x						x		SHT-SR _S -AA
T6510			x		x									SHT-SR _S -AA
T6511			x		x									SHT-SR _S -AA (Minor straightening after SR _S allowed)
T652										x				SHT-SR _C -AA
T73	x		x		x	x	x	x	x	x	x	x		SHT-AO
T7351		x				x						x		SHT-SR _S -AO
T73510				x	x									SHT-SR _S -AO
T73511			x		x									SHT-SR _S -AO (Minor straightening after SR _S allowed)
T7352										x	x			SHT-SR _C -AO
*T74										x	x			SHT-AO
*T7452										x	x	x		SHT-SR _C -AO
T76	x		x		x									SHT-AO (Less than T73 temper)
T7651		x												SHT-SR _S -AO
T76510					x									SHT-SR _S -AO
T76511					x									SHT-SR _S -AO (Minor straightening after SR _S allowed)
W511			x											SHT-SR _S
7076 - T6											x			SHT-AA

SAE AS1990 Revision B

TABLE 2 - Processes to Obtain Temper (Continued)

Alloy-Temper	Product Form S	Product Form P	Product Form TD	Product Form TE	Product Form E	Product Form RCF	Product Form BCF	Product Form WCF	Product Form R	Product Form F _H	Product Form F _D	Product Form RR	Product Form F	Process Used to Obtain Temper
7090 - T73511					x									SHT-SR _S -AO (Minor straightening after stretch allowed)
7091 - T73511					x									SHT-SR _S -AO (Minor straightening after stretch allowed)
7149 - T73														SHT-AO
T73511				x						x	x			SHT-SR _S -AO (Minor straightening after SR _S allowed)
7150 - T651		x												SHT-SR _S -AA
T6151		x												SHT-SR _S -AA _M
T6510					x									SHT-SR _S -AA
T6511					x									SHT-SR _S -AA (Minor straightening after SR _S allowed)
T61510					x									SHT-SR _S -AA _M
T61511					x									SHT-SR _S -AA _M (Minor straightening after SR _S allowed)
T7751		x			x									SHT-SR _S -AA _M
T77511				x										SHT-SR _S -AA _M (Minor straightening after SR _S allowed)
7175 - T6	x													SHT-AA
T62		x												Not available from producer - see A.2.2
T651		x												SHT-SR _S -AA
T66											x			SHT-AA _M
T73	x										x			SHT-AO
T7351		x												SHT-SR _S -AO
T73511					x									SHT-SR _S -AO (Minor straightening after SR _S allowed)
T7352										x				SHT-SR _C -AO
*T74										x				SHT-AO
*T7452										x				SHT-SR _C -AO
*T7454											x			SHT-SR _(S&C) -AO
T76	x													SHT-AO
T7651		x												SHT-SR _S -AO
7178 - H13								x						Cold worked approximately 1/4 to 1/2 hard
T6	x				x								x	SHT-AA
T62	x	x			x									Not available from producer - see A.2.2
T651		x												SHT-SR _S -AA