


SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions. SAE Executive Standards Committee provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."



REV.
D

TABLE 1 - PART NUMBERS AND DIMENSIONS

PART NO.	L	N MIN	M MAX	APPROX MASS LB/100	PART NO.	L	N MIN	M MAX	APPROX MASS LB/100
AS3244-04	.365- .385	.025	.099	1.04	AS3244-34	2.490-2.510	1.619	1.750	3.60
AS3244-05	.428- .448	.025	.099	1.11	AS3244-35	2.615-2.635	1.744	1.875	3.75
AS3244-06	.490- .510	.025	.099	1.18	AS3244-36	2.740-2.760	1.869	2.000	3.90
AS3244-07	.552- .572	.025	.099	1.27	AS3244-37	2.865-2.885	1.994	2.125	4.05
AS3244-08	.615- .635	.025	.099	1.34	AS3244-38	2.990-3.010	2.119	2.250	4.20
AS3244-09	.678- .698	.025	.099	1.41	AS3244-39	3.115-3.135	2.244	2.375	4.35
AS3244-10	.740- .760	.025	.099	1.48	AS3244-40	3.240-3.260	2.369	2.500	4.51
AS3244-11	.802- .822	.025	.099	1.57	AS3244-41	3.365-3.385	2.494	2.625	4.65
AS3244-12	.865- .885	.025	.125	1.64	AS3244-42	3.490-3.510	2.619	2.750	4.81
AS3244-13	.928- .948	.057	.188	1.71	AS3244-43	3.615-3.635	2.744	2.875	4.95
AS3244-14	.990-1.010	.119	.250	1.80	AS3244-44	3.740-3.760	2.869	3.000	5.11
AS3244-15	1.052-1.072	.181	.312	1.87	AS3244-45	3.865-3.885	2.994	3.125	5.25
AS3244-16	1.115-1.135	.244	.375	1.94	AS3244-46	3.990-4.010	3.119	3.250	5.41
AS3244-17	1.178-1.198	.307	.438	2.01	AS3244-47	4.115-4.135	3.244	3.375	5.55
AS3244-18	1.240-1.260	.369	.500	2.11	AS3244-48	4.240-4.260	3.369	3.500	5.71
AS3244-19	1.302-1.322	.431	.562	2.17	AS3244-49	4.365-4.385	3.494	3.625	5.87
AS3244-20	1.365-1.385	.494	.625	2.24	AS3244-50	4.490-4.510	3.619	3.750	6.01
AS3244-21	1.428-1.448	.557	.688	2.32	AS3244-51	4.615-4.635	3.744	3.875	6.17
AS3244-22	1.490-1.510	.619	.750	2.40	AS3244-52	4.740-4.760	3.869	4.000	6.31
AS3244-23	1.552-1.572	.681	.812	2.47	AS3244-53	4.865-4.885	3.994	4.125	6.47
AS3244-24	1.615-1.635	.744	.875	2.54	AS3244-54	4.990-5.010	4.119	4.250	6.61
AS3244-25	1.678-1.698	.807	.938	2.62	AS3244-55	5.115-5.135	4.244	4.375	6.77
AS3244-26	1.740-1.760	.869	1.000	2.70	AS3244-56	5.240-5.260	4.369	4.500	6.91
AS3244-27	1.802-1.822	.931	1.062	2.77	AS3244-57	5.365-5.385	4.494	4.625	7.07
AS3244-28	1.865-1.885	.994	1.125	2.84	AS3244-58	5.490-5.510	4.619	4.750	7.21
AS3244-29	1.928-1.948	1.057	1.188	2.92	AS3244-59	5.615-5.635	4.744	4.875	7.37
AS3244-30	1.990-2.010	1.119	1.250	3.00	AS3244-60	5.740-5.760	4.869	5.000	7.52
AS3244-31	2.115-2.135	1.244	1.375	3.15	AS3244-61	5.865-5.885	4.994	5.125	7.67
AS3244-32	2.240-2.260	1.369	1.500	3.30	AS3244-62	5.990-6.010	5.119	5.250	7.82
AS3244-33	2.365-2.385	1.494	1.625	3.45					

NOTES:

- FOR PART NUMBERS AS3244-04 THROUGH AS3244-18, THE THREAD PD (DATUM Z) SHALL REPLACE DATUM Y.
- MATERIAL: CORROSION AND HEAT RESISTANT NICKEL ALLOY PER AMS5662 (COMPOSITION SIMILAR TO UNS N07718).
- PROCUREMENT SPECIFICATION: AS7466.
- FLUORESCENT PENETRANT INSPECTION PER ASTM E1417/1417M, TYPE 1, SENSITIVITY LEVEL 2 MIN.
- SURFACE TEXTURE: SYMBOLS ARE PER ASME Y14.36M. REQUIREMENTS PER ASME B46.1. UNLESS OTHERWISE SPECIFIED, SURFACES TO BE 125 MICROINCHES Ra.
- BREAK SHARP EDGES .003 TO .015, UNLESS OTHERWISE SPECIFIED.
- DIMENSIONS ARE IN INCHES.
- DIMENSIONING AND TOLERANCING PER ASME Y14.5-2018.
- UNLESS OTHERWISE SPECIFIED, PART INVENTORY MANUFACTURED TO PREVIOUS REVISIONS OF THE APPLICABLE DRAWING OR SPECIFICATION MAY BE PROCURED AND USED UNTIL STOCK IS DEPLETED.
- DO NOT USE UNASSIGNED PART NUMBERS.

	AEROSPACE STANDARD	AS3244™ SHEET 2 OF 3	REV. D
	BOLT, MACHINE - DOUBLE HEXAGON EXTENDED WASHER HEAD, DRILLED, PD SHANK, NICKEL ALLOY, UNS N07718, 185 KSI MIN UTS, 2500-28 UNJF-3A		