

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

REV.
E

AS3563™

FEDERAL SUPPLY CLASS
5310

RATIONALE

RESTRUCTURE NOTES 1, 2 AND 3 FOR CLARITY AND ADD EXCEPTION FOR RECRYSTALLIZED MICROSTRUCTURE, ADD NEW NOTE FOR DISPOSITION OF EXISTING INVENTORY, GENERAL EDITORIAL AND FORMAT CHANGES.





FIGURE 1 - NUT

For more information on this standard, visit
<https://www.sae.org/standards/content/AS3563E/>

THIRD ANGLE PROJECTION



CUSTODIAN: E-25

PROCUREMENT SPECIFICATION: AS4393 /2/



AEROSPACE STANDARD

NUT, SELF-LOCKING, DOUBLE HEXAGON, SOLID
FILM LUBRICATED, EXTENDED WRENCH PAD,
160 KSI, 800 °F, UNS S66286

AS3563™
SHEET 1 OF 3

REV.
E

TABLE 1A - PART NUMBERS AND DIMENSIONS D, B, AS870 DASH NO., E, F, AB, H, AND K

PART NUMBER	THREAD D	B NOM	AS870 DASH NO.	ØE MAX	ØF MIN	ØAB	H MIN	K MAX
AS3563-09	.1900-32UNJF-3B	.2500	08	.340	.325	.190-.220	.045	.305
AS3563-10	.2500-28UNJF-3B	.3125	10	.450	.410	.250-.280	.045	.400
AS3563-11	.3125-24UNJF-3B	.3750	12	.525	.495	.312-.342	.060	.455
AS3563-12	.3750-24UNJF-3B	.4375	14	.600	.560	.375-.405	.070	.520
AS3563-13	.4375-20UNJF-3B	.5625	18	.690	.650	.438-.468	.080	.595
AS3563-14	.5000-20UNJF-3B	.6250	20	.780	.740	.500-.532	.100	.680
AS3563-15	.5625-18UNJF-3B	.6875	22	.880	.840	.562-.597	.110	.758
AS3563-16	.6250-18UNJF-3B	.7812	25	.970	.925	.625-.660	.120	.850
AS3563-17	.7500-16UNJF-3B	.9375	30	1.230	1.180	.750-.785	.130	1.032

TABLE 1B - DIMENSIONS L, N, T, P, R, AH, AND APPROX MASS

PART NUMBER	ØL	ØN MAX	T MIN	P	R	AH	APPROX MASS LB/100
AS3563-09	.190-.210	.262	.082	.004	.006	.0014	.28
AS3563-10	.250-.270	.326	.130	.005	.007	.0014	.51
AS3563-11	.312-.332	.392	.170	.005	.008	.0016	.83
AS3563-12	.375-.395	.458	.210	.005	.009	.0016	1.34
AS3563-13	.438-.458	.588	.230	.005	.010	.0020	2.74
AS3563-14	.500-.520	.654	.260	.006	.012	.0020	3.34
AS3563-15	.562-.582	.720	.320	.006	.014	.0020	4.92
AS3563-16	.625-.645	.817	.370	.007	.015	.0020	7.12
AS3563-17	.750-.770	.980	.500	.007	.016	.0020	13.01

NOTES:

1. MATERIAL: CORROSION AND HEAT RESISTANT STEEL PER AMS5731 OR AMS5734 (COMPOSITION SIMILAR TO UNS S66286).
- 2/ PROCUREMENT SPECIFICATION: AS4393 EXCEPT AS FOLLOWS:
 - a. HEAT TREATMENT: AFTER FORMING, NUTS SHALL BE HEAT TREATED PER AMS2759/3 TO MEET THE HARDNESS SPECIFIED IN NOTE 2g.
 - b. COATING: SOLID FILM LUBRICANT PER AS1701, TYPE VI, IN LIEU OF SILVER PLATE PER AMS2411.
 - c. PRETREATMENT: PRIOR TO APPLYING THE SOLID FILM LUBRICANT, NUTS MAY BE PLATED WITH COPPER (AMS2418) OR NICKEL (AMS2403) OR BOTH TO .00025 MAXIMUM THICKNESS.
 - d. DIMENSIONS APPLY AFTER PRETREATMENT PLATING AND BEFORE COATING WITH SOLID FILM LUBRICANT.
 - e. BAKE AT 800 °F ± 15 °F IN LIEU OF 1200 °F FOR NUTS TESTED AFTER BAKE.
 - f. COMPLETELY RECRYSTALLIZED MICROSTRUCTURE IS NOT REQUIRED.
 - g. HARDNESS: 32-42 HRC.
3. BREAK SHARP EDGES .003 TO .015, UNLESS OTHERWISE SPECIFIED.
4. FLUORESCENT PENETRANT INSPECTION PER ASTM E1417/E1417M, TYPE 1, SENSITIVITY LEVEL 2 MIN, PRIOR TO PRETREATMENT OR COATING. ACCEPTANCE CRITERIA PER AS3071.

	AEROSPACE STANDARD	AS3563™ SHEET 2 OF 3	REV. E
	NUT, SELF-LOCKING, DOUBLE HEXAGON, SOLID FILM LUBRICATED, EXTENDED WRENCH PAD, 160 KSI, 800 °F, UNS S66286		