

AEROSPACE STANDARD

SAE AS5272

REV.
A

Issued 1997-03
Reaffirmed 2001-10
Revised 2005-07

Superseding AS5272

(R) Lubricant, Solid Film, Heat Cured,
Corrosion Inhibiting
Procurement Specification

1. SCOPE:

This SAE Aerospace Standard (AS) establishes the requirements for heat cured solid film lubricants. For other general or high temperature applications, see AS1701.

1.1 Application:

For applications where temperatures may range from -90 to 400 °F (-68 to 204 °C).

1.2 Type:

This specification establishes the following types:

Type I: A lubricant capable of being cured within 60 minutes at 302 °F $\pm$ 27 °F (150 °C $\pm$ 15 °C) with an endurance life of 250 minutes minimum. See 6.4 for related product information.

Type II: A lubricant capable of being cured within 60 minutes at 400 °F $\pm$ 27 °F (204 °C $\pm$ 15 °C) with an endurance life of 450 minutes minimum. See 6.4 for related product information.

Type III: A low volatile organic compound (VOC) content lubricant capable of being cured within 120 minutes at 302 °F $\pm$ 27 °F (150 °C $\pm$ 15 °C) or within 60 minutes at 400 °F $\pm$ 27 °F (204 °C $\pm$ 15 °C) with an endurance life of 450 minutes minimum. Type III shall be used when performance is satisfactory for the desired application to meet VOC emission regulations.

Color 1 - Natural product color.

Color 2 - Black color. See 3.7.

See 6.4 for related product information.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2005 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER:

Tel: 877-606-7323 (inside USA and Canada)

Tel: 724-776-4970 (outside USA)

Fax: 724-776-0790

Email: custsvc@sae.org

SAE WEB ADDRESS:

<http://www.sae.org>

SAE AS5272 Revision A

1.3 Safety - Hazardous Materials:

While the materials, methods, applications, and processes described or referenced in this specification may involve use of hazardous materials, this specification does not address the hazards which may be involved in such use. The product manufacturer shall prepare Materials Safety Data Sheets (MSDS) in accordance with AMS 2825 and abide by MSDS requirements to ensure familiarity with the safe and proper handling of hazardous materials used and take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. REFERENCES:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order. In the event of conflict between the text of this specification and references cited herein, the text of this specification takes precedence.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS-QQ-A-250/5	Aluminum Alloy, Alclad 2024, Plate and Sheet
AMS 1424	Deicing/Anti-Icing Fluid, Aircraft SAE Type I
AMS 2825	Material Safety Data Sheets
AS1701	Lubricants, Solid Dry Film
AS5528	Lubricant Application, Solid Film, Heat Cured, Corrosion Inhibiting
AS9100	Quality Systems - Aerospace - Model for Quality Assurance in Design, Development, Production, Installation and Servicing

2.2 AIA Publications:

Available from AIA of America, Inc., 1250 Eye Street NW, Washington, DC 20005.

NAS850	General Packaging Standard
NAS854	Hazardous Material Packaging and Safety Data Sheet Preparation

SAE AS5272 Revision A

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-PRF-372	Cleaning Compound, Solvent for Bore of Small Arms and Automatic Aircraft Weapons
FED-STD-595	Colors used Government Procurement
FED-STD-791	Lubricants, Liquid Fuels, and Related Products, Methods of Testing
VV-D-1078	Damping Fluid, Silicone Base (Dimethyl Polysiloxane)
MIL-A-8625	Anodic Coatings, for Aluminum and Aluminum Alloys
MIL-PRF-14107	Lubricating Oil, Weapons, Low Temperature
MIL-DTL-16232	Phosphate Coatings, Heavy, Manganese or Zinc Base (for Ferrous Metals)
MIL-PRF-23699	Lubricating Oil, Aircraft Turbine Engine, Synthetic Base, NATO Code Number 0-156
MIL-L-46000	Lubricant, Semi-Fluid, (Automatic Weapon)
MIL-PRF-46010F	Lubricant, Solid Film, Heat Cured, Corrosion Inhibiting
MIL-PRF-63460	Lubricant, Cleaner and Preservative for Weapons and Weapon Systems
MIL-C-81302	Cleaning, Compound, Solvent, Trichlorotrifluoroethane
MIL-T-81533	Trichloroethane 1,1,1, (Methyl Chloroform) Inhibited, Vapor Degreasing
MIL-DTL-83133	Turbine Fuel, Aviation, Kerosene Types
MIL-PRF-83282	Hydraulic Fluid, Fire Resistant, Synthetic Hydrocarbon Base, Metric, NATO Code Number H-537
MIL-PRF-85336	Lubricant, All Weather (Automatic Weapons)

SAE AS5272 Revision A

2.3 (Continued):

Available from www.osha.gov

HSC 29 CFR 1910.1200 Hazard Communication, Toxic and Hazardous Substances

2.4 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM A 108	Standard Specification for Steel Bars, Carbon, Cold-Finish, Standard Quality
ASTM A 167	Standard Specification for Stainless and Heat-Resisting Chromium-Nickel-Steel Plate, Sheet and Strip
ASTM B 117	Standard Practice for Operating Salt Spray (Fog) Test Apparatus
ASTM B 244	Standard Test Method for Measurement of Thickness of Anodic Coatings on Aluminum and Other Nonconductive Coatings on Nonmagnetic Basis Metals with Eddy Current Instruments
ASTM B 499	Standard Test Method for Measurements of Coating Thicknesses by the Magnetic Method: Nonmagnetic Coatings on Magnetic Basis Metals
ASTM D 56	Standard Test Method for Flash Point by Tag Closed Tester
ASTM D 1141	Standard Practice for Preparation of Substitute Ocean Water
ASTM D 1186	Standard Test Method for Nondestructive Measurement of Dry Film Thickness of Nonmagnetic Coatings Applied to a Ferrous Base
ASTM D 1193	Standard Specification for Reagent Water
ASTM D 1400	Standard Test Method for Nondestructive Measurement of Dry Film Thickness of Nonconductive Coatings Applied to a Nonferrous Metal Base

SAE AS5272 Revision A

2.4 (Continued):

ASTM E 1252	Standard Practice for General Techniques for Obtaining Infrared Spectra for Qualitative Analysis
ASTM D 2510	Standard Test Method for Adhesion of Solid Film Lubricants
ASTM D 2511	Standard Test Method for Thermal Shock Sensitivity of Solid Film Lubricants
ASTM D 2625	Standard Test Method for Endurance (Wear) Life and Load-Carrying Capacity of Solid Film Lubricants (Falex Pin on Vee Method)
ASTM D 2649	Standard Test Method for Corrosion Characteristics of Solid Film Lubricants
ASTM D 2832	Standard Guide for Determining Volatile and Nonvolatile Content of Paint and related Coatings
ASTM D 3735	Standard Specification for VM&P Naphthas
ASTM D 3960	Standard Practice for Determining Volatile Organic Compound (VOC) Content of Paints and Related Coatings
ASTM D 4017	Standard Test Method for Water in Paints and Paint Materials by Karl Fischer Method
ASTM D 4457	Standard Test Methods for Determination of Dichloromethane and 1,1,1-Trichloroethane in Paints and Coatings by Direct Injection into a Gas Chromatograph
ASTM F 22	Standard Test Method for Hydrophobic Surface Films by the Water-Break Test

SAE AS5272 Revision A

2.5 PRI Publications:

Available from Performance Review Institute, 161 Thornhill Road, Warrendale, PA 15086-7527 (www.pri.sae.org).

PD2001	Qualified Product Management Council Procedures for Qualified Products Group
PRI-QPL-AS5272	Qualified Products List (QPL) of Products Qualified Under SAE Aerospace Specification AS5272 - Lubricant, Solid Film, Heat Cured, Corrosion Inhibiting

2.6 ISO Publications:

ISO/IEC 17025	General Requirements for the Competence of Testing and Calibration Laboratories
---------------	---

3. REQUIREMENTS:

3.1 Qualification:

The lubricants furnished under this specification shall be products, which are listed or approved for listing on the applicable qualified product list, PRI-QPL-AS5272. This QPL requirement shall be in effect two years after the date of issuance of AS5272 Revision A, dated July 2005. No change in product formulation, raw material, basic methods of manufacturing or plant site shall be made without notification and prior approval from the Performance Review Institute (PRI). Requalification or testing and revised supplier designation may be required.

3.1.1 Manufacturer Qualification: A manufacturer producing a product in conformance to this procurement specification shall be accredited in accordance with AS9100.

3.1.2 Product Qualification: All lubricants shall conform to the requirements of this specification and shall be approved in accordance with the requirements of PD2001, for listing in a PRI Qualified Products List (QPL) PRI-QPL-AS5272.

3.1.3 Qualification Testing: All qualification testing shall be conducted by a laboratory which is accredited per ISO/IEC 17025.

3.2 Materials:

Component materials used in the manufacture of this lubricant shall consist essentially of finely powdered lubricating solids dispersed in a suitable liquid binder. The lubricant shall contain no graphite, powdered metal, or ozone depleting substances. Recycled materials may be used provided the lubricant meets the requirements of the specification. The lubricant shall be suitable for application by brushing, dipping, or spraying. The applied film for Type I shall be capable of being cured within 60 minutes at $302^{\circ}\text{F} \pm 27^{\circ}\text{F}$ ($150^{\circ}\text{C} \pm 15^{\circ}\text{C}$). The applied film for Type II shall be capable of being cured within 60 minutes at $400^{\circ}\text{F} \pm 27^{\circ}\text{F}$ ($204^{\circ}\text{C} \pm 15^{\circ}\text{C}$). The applied film for Type III shall be capable of being cured within 60 minutes at $400^{\circ}\text{F} \pm 27^{\circ}\text{F}$ ($204^{\circ}\text{C} \pm 15^{\circ}\text{C}$), or within 120 minutes at $302^{\circ}\text{F} \pm 27^{\circ}\text{F}$ ($150^{\circ}\text{C} \pm 15^{\circ}\text{C}$), and be of such a nature that it shall conform to the requirements of this specification when cured at either temperature. All reference cure temperatures reflect the temperature that the part must obtain prior to the start of the cure cycle. Type III shall be a low VOC material in accordance with 3.4.11. The contractor shall certify that if any carcinogenic or potentially carcinogenic constituents are present as defined under the Hazard Communication Standards (HCS) 29 CFR 1910.1200, appropriate warnings (see HCS 29 CFR 1910.1200) shall be included on the product label.

3.3 Film Appearance and Thickness:

The bonded solid film lubricant, when examined as specified in 4.6.2, shall be uniform in color, smooth, free from any cracks, scratches to base metal, pinholes, blisters, bubbles, runs, sags, foreign matter, grit, rough particles, or separation of ingredients. The average thickness, based on 6 readings minimum, of the cured film for all Types shall be between 0.0003 in (0.008 mm) and 0.0005 in (0.013 mm), with no single reading less than 0.0002 in (0.005 mm) or greater than 0.0007 in (0.018 mm).

3.4 Performance Characteristics:

- 3.4.1 Film Adhesion: The bonded solid film lubricant, when tested as specified in Table 2, shall not be lifted to expose any bare metal surface. A uniform deposit of powdery material clinging to the tape is acceptable.
- 3.4.2 Resistance to Fluids: The bonded solid film lubricant, when tested as specified in Table 2, after immersion in each of the fluids as specified in Table 3, shall not be lifted by the tape to expose any bare metal surface; nor shall the solid film lubricant lift, blister, crack, or peel. A uniform deposit of powdery material clinging to the tape is acceptable.
- 3.4.3 Thermal Stability: The thermal stability of the bonded solid film lubricant shall be such that, when tested as specified in Table 2, the film shall not flake, crack, or lift and shall conform to the requirements for film adhesion (see 3.4.1).

SAE AS5272 Revision A

- 3.4.4 Endurance Wear Life: When tested in four trials in accordance with Table 2, the bonded solid film lubricant shall have an average endurance life at 1000 pounds (lbf) as follows:

Type I: 250 minutes with no single test less than 210 minutes

Type II and III: 450 minutes with no single test less than 390 minutes

- 3.4.5 Load Carrying Capacity: When tested in two trials in accordance with Table 2, the bonded solid film shall have the following average capacity:

Type I and III: 2500 lbf (11,120 N) with no single test less than 2250 lbf (10,000 N).

Type II: 2000 lbf (8900 N) with no single test less than 1750 lbf (7780 N).

- 3.4.6 Aluminum Corrosion Resistance (Type I and III): When subjected to heat and humidity conditions as specified in 4.5, the bonded solid film lubricant on anodized aluminum panels as specified in 4.5.2.1 shall not show or cause discoloration, pitting, formation of white deposits, or other evidence of corrosion.

- 3.4.7 Sulfurous Acid-Salt Spray (Type I and III): When applied to steel panels as specified in 4.5.2.2 and exposed to sulfurous acid-salt spray in accordance with Table 2, there shall be no resultant pitting, visible corrosion, or staining.

- 3.4.8 Salt-Spray (Fog) Test (Type II and III): The lubricant, after being applied to steel panels as specified in 4.5.2.2 shall show no more than three rust spots per panel, none greater than 0.039 (1.0 mm) in diameter after 100 hours exposure to a 5% salt spray solution in a salt fog cabinet in accordance with ASTM B 117 and Table 2.

- 3.4.9 Solids Content: The lubricant shall contain not less than 40% by weight when tested as specified in 4.6.3.

- 3.4.10 Storage Stability: The fluid lubricant, after a minimum storage period as specified in 4.6.4, shall conform to the requirements for endurance life (see 3.4.4) and the sulfurous acid-salt spray (see 3.4.7) for Type I and III or the salt-spray (fog) test (see 3.4.8) for Type II and III when tested as specified in 4.6.

- 3.4.11 Volatile Organic Compound (Type III): The lubricant shall contain not more than 250 g/L of volatile organic content when tested as specified in 4.6.5.

3.5 Toxicity:

The lubricant shall have no adverse effects on human health when it is used as intended. Questions on toxicology shall be referred by the procuring activity to the appropriate departmental medical service after consulting the qualifying activity. A Material Safety Data Sheet shall be submitted as specified in 1.3.

SAE AS5272 Revision A

3.6 Application, Manufactured Parts:

The lubricant shall be applied in accordance with AS5528, unless otherwise specified by the purchaser.

3.7 Color (Type III):

The lubricant supplied in Color 2 shall closely match color no. 37038 of FED-STD-595, but shall not be lighter than gray no. 36076 of FED-STD-595.

3.8 Restricted Materials (Type III):

The lubricant shall not contain lead, lead-containing compounds, graphite, powdered metal, or ozone-depleting substances in either liquid or cured form (see 4.6.1).

3.9 Chemical Characterization Analysis:

The lubricant shall be subject to chemical characterization in accordance with 4.7.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The manufacturer is responsible for performing all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, and unless disapproved by the purchaser, the manufacturer's own or any other facilities suitable for the performance of the inspection requirements specified herein, may be used. The procuring activity reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to assure supplies and services conform to the prescribed requirements.

- 4.1.1 Responsibility for Compliance: All items shall meet all requirements of Sections 3 and 5. The inspection set forth in this specification shall become part of the manufacturer's overall inspection system or quality program. The absence of any inspection requirements in this specification shall not relieve the manufacturer of the responsibility of assuring that all products or supplies submitted to the procuring activity for acceptance comply with all requirements of the contract or purchase order. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the procuring activity to acceptance of defective material.

SAE AS5272 Revision A

4.2 Classification of Inspections:

The inspections specified herein are classified as follows:

- a. Qualification Inspection (see 4.3).
- b. Quality Conformance Inspection (see 4.4).

4.3 Qualification Inspection:

The qualification inspection performed by the qualification laboratory shall consist of approval of the manufacturer's submitted report, subjecting the qualification sample, 4.3.1, to examination and testing for all the requirements of this specification.

- 4.3.1 Qualification Samples: The qualification samples shall consist of 4 quarts (4 liters) of lubricant from one batch, and two copies of the supplier's report for the product for which qualification is desired. The report shall show the product inspection results for all the requirements of this specification and shall refer specifically to the applicable paragraphs in the specification. The samples, reports and Material Safety Data Sheets (see 1.3) for the product shall be forwarded in accordance with Section 5.

Sample for qualification inspection

LUBRICANT, SOLID FILM, HEAT CURED, CORROSION INHIBITING, Type I, Type II, or Type III, as applicable.

Name of manufacturer.

Product code/batch number.

Date of manufacture.

Copy of the Fourier Transform Infrared analysis report. See 4.7.

Submitted by (name) (date) for qualification inspection in accordance with AS5272 including revision letter, under authorization of (reference authorizing letter).

- 4.3.2 Retention of Qualification: In order to retain qualification of a product approved for listing on the qualified products list (QPL), the manufacturer shall verify by certification to PRI that the manufacturer's product complies with the requirements of this specification. The time of periodic verification by certification shall be in five-year intervals from the date of original qualification. The PRI in conjunction with the Qualified Products Group (QPG) reserves the right to re-examine the qualified product whenever deemed necessary to determine that the product continues to meet any or all of the specification requirements.

4.4 Quality Conformance Inspection:

The quality conformance inspection shall consist of inspection of samples for tests (see 4.4.2) for all of the tests specified in Table 2, except for resistance to fluids (see 3.4.2), thermal stability (see 3.4.3), aluminum corrosion resistance (see 3.4.6), storage stability (see 3.4.10), and chemical characterization analysis (see 3.9) and inspection of samples of filled containers (see 4.4.3) for compliance to Section 5. Samples shall be labeled completely with information identifying the purpose of the sample, name of the product, specification number, batch number, date of sampling, and contract or purchase number.

- 4.4.1 Batch: A batch is defined as the end product of all the raw materials mixed or blended in a single operation.
- 4.4.2 Samples for Tests: The sample for test shall consist of four separate quarts (liters) of lubricant selected at random from each batch of lubricant. The lot shall be unacceptable if a sample fails to meet any of the test requirements specified.
- 4.4.3 Sample for Examination of Filled Containers: A random sample of filled containers shall be selected from each batch of lubricant in accordance with Table 1. Acceptance quality shall be based on zero defectives.

TABLE 1

Batch Size (No. of containers)	Sample Size (No. of containers)
1	1
2 to 8	2
9 to 15	3
16 to 25	5
26 to 50	8
51 to 90	13
91 to 150	20
151 to 280	32
281 to 500	50
501 to 1200	80

4.5 Inspection Conditions:

- 4.5.1 Atmospheric Conditions: Unless otherwise specified, all examinations and tests shall be performed at a temperature of $77^{\circ}\text{F} \pm 5^{\circ}\text{F}$ ($25^{\circ}\text{C} \pm 3^{\circ}\text{C}$) and at a relative humidity between 30 and 70%.

4.5.2 Preparation of Test Panels:

- 4.5.2.1 Preparation of and Application to Test Panels for Type I and Type III Solid Film Lubricant (Aluminum and CRES): The panels shall be made from aluminum alloy conforming to AMS-QQ-A-250/5, condition T6X or T8XX, anodized to conform to MIL-A-8625, Type II sulfuric acid anodize, and measuring approximately 0.020 in (0.05 cm) by 3.00 in (7.6 cm) by 6.00 in (15.2 cm); and corrosion resistant steel conforming to ASTM A 167, and measuring approximately 0.035 in (0.09 cm) by 3.00 in (7.6 cm) by 6.00 in (15.2 cm). The panels shall be pre-cleaned with aliphatic naphtha conforming to ASTM D 3735 that sufficiently cleans surfaces to pass ASTM F 22. This cleaner shall not cause damage; i.e., pitting, etching, etc. to the surface being cleaned. The corrosion resistant steel panels shall have both faces and all edges grit-blasted with 180 to 220 grit aluminum oxide. Only one side of each panel shall be fully coated, except for two of the anodized aluminum panels which shall have the lubricant applied to a 1.00 in (2.54 cm) wide strip to enable measurement of the film thickness. A spray application technique shall be used to coat the panel for the tests specified herein. The solid film lubricant average thickness, based on 6 readings minimum, after cure, shall be 0.0003 in (0.008 mm) to 0.0005 in (0.013 mm), with no single reading less than 0.0002 in (0.005 mm) or greater than 0.0007 in (0.018 mm). Three coats shall be the maximum number required to obtain the desired film thickness. Air drying at $77^{\circ}\text{F} \pm 5^{\circ}\text{F}$ ($25^{\circ}\text{C} \pm 3^{\circ}\text{C}$) for 10 minutes between coats is allowed. After the final coat has been applied, the coated specimens shall be allowed to air dry for 30 minutes minimum for Type I and 60 minutes minimum for Type III, a flash cure at 149 to 174°F (65 to 79°C) for 10 to 30 minutes until dry to the touch is also permitted. The coated specimens shall then be placed in an air circulating oven at $302^{\circ}\text{F} \pm 27^{\circ}\text{F}$ ($150^{\circ}\text{C} \pm 15^{\circ}\text{C}$) for 1 hour for Type I, or 2 hours for Type III. The coated specimens shall be removed from the oven and allowed to cool to room temperature. At least two test panel specimens shall be used in each test method. A total of 30 aluminum panels and two corrosion resistant steel panels are required for testing in accordance with performance requirements of this specification.

4.5.2.2 Preparation of and Application to Test Specimens for Type I, Type II and Type III Solid Film Lubricant (Steel): The steel panels shall be approximately 0.126 in (0.32 cm) by 3.00 in (7.6 cm) by 6.00 in (15.2 cm) conforming to ASTM A 108. The panels shall be pre-cleaned with aliphatic naphtha conforming to ASTM D 3735 that sufficiently cleans surfaces to pass ASTM F 22. This cleaner shall not cause damage; i.e., hydrogen embrittlement, etc. to the surface being cleaned. The steel panels shall have both faces and all edges grit-blasted with 180 to 220 grit aluminum oxide. Phosphate the panels, weight should be 11 to 22 g/m², in accordance with MIL-DTL-16232, using ASTM B 499 or ASTM D 1186 to measure the thickness of the phosphated panels. The steel panels shall be dipped or sprayed to the same thickness as specified for the aluminum panels, see 4.5.2.1. After air drying 30 minutes minimum for Type I and II or 60 minutes minimum for Type III, a flash cure at 149 to 174 °F (65 to 79 °C) for 10 to 30 minutes until dry to the touch is also permitted, bake the panels in an air circulating oven at 302 °F ± 27 °F (150 °C ± 15 °C), Type I, or 400 °F ± 27 °F (204 °C ± 15 °C), Type II and III for 1 hour. The coated specimens shall be removed from the oven and allowed to cool to room temperature. At least two test panels shall be used in each test method. A total of two steel panels and six sets of pins and vee-blocks (3.4.4 and 3.4.5) are required for testing in accordance with the performance requirements of this specification.

4.6 Methods of Inspection:

Methods of inspection shall be in accordance with Table 2 and 4.6.1 through 4.6.5.

- 4.6.1 Restricted Materials (Type III): The contractor shall submit for PRI approval, certification that no graphite, powdered metal, lead or lead containing compounds, or ozone depleting substances are present in the product furnished under this specification.
- 4.6.2 Film Appearance and Thickness: The bonded solid film lubricant specimens shall be examined visually and microscopically at magnification of 12-15X for uniformity in color, smoothness, evidence of cracks, scratches, pinholes, blisters, bubbles, runs, sags, foreign matter, grit, rough particles, and separation of ingredients. Film thickness shall be in accordance with Table 2.
- 4.6.3 Solids Content: Stir the lubricant thoroughly, weigh 5.0 ± 0.5 grams into a disposable weighing dish, (Fisher Scientific catalog number 08 to 732, or equivalent). Place the dish and contents into a forced draft oven maintained at a temperature of 120 °F ± 5 °F (49 °C ± 3 °C) for 18 hours ± 1 hour. Remove from oven and place in desiccator. Raise temperature of oven to 400 °F ± 5 °F (204 °C ± 3 °C) and replace dish with residue into 400 °F ± 5 °F (204 °C ± 3 °C) oven for 1 additional hour. Remove dish and contents and cool in a desiccator. When cool, weigh dish and contents. Calculate percent by weight of solids in fluid lubricant as shown in Equation 1:

$$\text{Percent total solids} = \frac{\text{Weight of solid materials (grams)}}{\text{Weight of sample (grams)}} \times 100 \quad (\text{Eq. 1})$$

SAE AS5272 Revision A

TABLE 2 - Quality Performance Inspection Tests

Characteristic	Test Methods Government	Test Methods ASTM	Requirement Paragraph
Film Thickness ¹			3.3
Aluminum		D 1400 or B 244	
Steel		D 1186 or B 499	
Film Adhesion		D 2510 ⁷ Procedure A	3.4.1
Resistant to Fluids ²		D 2510 ⁷ Procedure C	3.4.2
Thermal Stability ³		D 2511	3.4.3
Endurance Wear Life ⁴		D 2625 ⁷ Procedure A	3.4.4
Load Carrying Capacity ⁴		D 2625 ⁷ Procedure B	3.4.5
Aluminum Corrosion ⁵		D 2649	3.4.6
Sulfurous Acid/Salt Fog ⁶	FED-STD-791 ⁷		3.4.7
Salt Spray (Fog) ⁵		B 117	3.4.8
Solid Content (See 4.6.3)			3.4.9
Storage Stability	FED-STD-791 ⁷		3.4.10
Volatile Organic		D 3960, D 2832	3.4.11
Compound Content		D 4017, D 4457	
Chemical Characterization Analysis		E 1252 (See 4.7)	3.9

¹ Film thickness is determined after panels are prepared in accordance with sections 4.5.2.1 and 4.5.2.2.

² Test fluids shall be in accordance with Table 3.

³ Any condensation shall be removed with clean, dry compressed air. The dried panel shall then be subjected to the film adhesion test.

⁴ The surface of test pins and vee-blocks shall be grit blasted using 180 to 220 grit aluminum oxide to a surface roughness of 50 to 60 RMS. The surface shall then be cleaned and pretreated with phosphate in accordance with MIL-DTL-16232, Type Z or Type M, Class 3 with a weight of 11 to 22 g/m².

⁵ All lubricant film thicknesses must conform to 3.3 when prepared in accordance with 4.5.2 before placing in salt fog cabinet in accordance with ASTM B 117.

⁶ The panels shall be subjected to four cycles. Each cycle shall consist of 2 hours spray time and 24 hours drying time before inspection.

⁷ When performing ASTM D 2510, ASTM D 2625, or FED-STD-791 test methods, use Aliphatic Naphtha conforming to ASTM D 3735 followed by acetone or any environmentally safe cleaner that sufficiently cleans surfaces to pass ASTM F 22 (MIL-C-81302, Trichlorotrifluoroethane, or MIL-T-81533, 1,1,1-Trichloroethane are not acceptable cleaners for testing or production).

NOTE: The cleaner used becomes part of the supplier's process and no change shall be made without notification and prior approval from the responsible QPL agency.