

AEROSPACE STANDARD

SAE AS666

REV.
C

Issued	1963-11
Revised	1982-05
Noncurrent	2005-01

Cavity Design and O-ring Selection for Static Seal Use in Aircraft Tubeless Tire Wheels

NONCURRENT NOTICE

This specification has been declared "NONCURRENT" as of January 2005. It is recommended, therefore, that this document not be specified for new designs.

Each of these "NONCURRENT" documents is available from SAE.

Document made inactive for new designs. Committee feels that the practice amongst wheel manufacturers is to use proprietary gland standards and materials to improve seal integrity rendering this document obsolete for new design. This document shall be retained for historical record only.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2005 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER:

Tel: 877-606-7323 (inside USA and Canada)

Tel: 724-776-4970 (outside USA)

Fax: 724-776-0790

Email: custsvc@sae.org

SAE WEB ADDRESS:

<http://www.sae.org>

SAE AS666 Revision C

1. PURPOSE: This Aerospace Standard (AS) establishes design practices for aircraft tubeless tire wheel static seals.
2. SCOPE: This AS applies to the cavity design and the selection of O-rings for tubeless tire wheels.
3. O-RING CAVITY DESIGN:
 - 3.1 For use with 0.103 cross-section diameter O-ring, See Figure 1, page 3.
 - 3.2 For use with 0.139 cross-section diameter O-ring, See Figure 1, page 3.
 - 3.3 For use with 0.210 cross-section diameter O-ring, See Figure 1, page 3.
 - 3.4 For use with 0.275 cross-section diameter O-ring, See Figure 1, page 3.
 - 3.5 O-ring contact surfaces shall not exceed a maximum roughness of 63 RHR.

CAUTION

Care should be taken to prevent excessive and/or rough paint on O-ring contact surfaces which will prevent sealing.

- 3.6 Refer to MIL-P-5514 for static seal cavity design for use with demountable flange wheels.

SAE AS666 Revision C

4. O-RING SELECTION:

- 4.1 Material from MIL-P-25732 or MIL-P-5516 is recommended for use in this type seal.
- 4.2 O-ring stretch should be limited to 3 to 8 percent of nominal ID in the installed position.
- 4.3 See AS 568 for O-ring sizes and corresponding dash number.

PREPARED BY
SUBCOMMITTEE A-5A, WHEELS, BRAKES & SKID CONTROLS OF COMMITTEE A-5,
AEROSPACE LANDING GEAR SYSTEMS