

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AS7351

FEDERAL SUPPLY CLASS
5340

RATIONALE

THIS DOCUMENT HAS BEEN REAFFIRMED TO COMPLY WITH THE SAE 5-YEAR REVIEW POLICY.

NOTICE


THIS DOCUMENT HAS BEEN TAKEN DIRECTLY FROM U.S. MILITARY SPECIFICATION AN735 REV 5 NOTICE 1 AND CONTAINS ONLY MINOR EDITORIAL AND FORMAT CHANGES REQUIRED TO BRING IT INTO CONFORMANCE WITH THE PUBLISHING REQUIREMENTS OF SAE TECHNICAL STANDARDS. THE INITIAL RELEASE OF THIS DOCUMENT IS INTENDED TO REPLACE AN735 REV 5 NOTICE 1. ANY PART NUMBERS ESTABLISHED BY THE ORIGINAL SPECIFICATION REMAIN UNCHANGED.

THE ORIGINAL MILITARY SPECIFICATION WAS ADOPTED AS AN SAE STANDARD UNDER THE PROVISIONS OF THE SAE TECHNICAL STANDARDS BOARD (TSB) RULES AND REGULATIONS (TSB 001) PERTAINING TO ACCELERATED ADOPTION OF GOVERNMENT SPECIFICATIONS AND STANDARDS. TSB RULES PROVIDE FOR (A) THE PUBLICATION OF PORTIONS OF UNREVISED GOVERNMENT SPECIFICATIONS AND STANDARDS WITHOUT CONSENSUS VOTING AT THE SAE COMMITTEE LEVEL, AND (B) THE USE OF THE EXISTING GOVERNMENT SPECIFICATION OR STANDARD FORMAT.

ANY MATERIAL RELATING TO QUALIFIED PRODUCT LISTS HAS NOT BEEN ADOPTED BY SAE. THIS MATERIAL WAS PART OF THE ORIGINAL MILITARY SPECIFICATION AND IS REPRINTED HERE FOR HISTORIC REFERENCE ONLY.

SAENORM.COM : Click to view the full PDF of as7351

THIRD ANGLE PROJECTION



PREPARED BY COMMITTEE E-25

PROCUREMENT SPECIFICATION: NONE

SAE Aerospace
An SAE International Group


AEROSPACE STANDARD

CLAMP, LOOP TYPE BONDING

AS7351
SHEET 1 OF 3

ISSUED 1998-05 REAFFIRMED 2007-06

AS7351



DASH NUMBERS	DIMENSIONS		LBS. PER 100 PCS (APPROX)	
	'D' DIA. +.005	'E' +.015	STEEL AND CRES	ALUM ALLOY.
2	.125	.313	.24	.08
3	.188	.344	.31	.11
4	.250	.375	.37	.13
5	.313	.406	.44	.15
6	.375	.469	.52	.18
7	.438	.500	.59	.20
8	.500	.531	.65	.22
9	.563	.563	.72	.25
10	.625	.594	.78	.27
11	.688	.625	.85	.29
12	.750	.656	.91	.31
13	.813	.688	.98	.34
14	.875	.719	1.04	.36
15	.938	.750	1.10	.38
16	1.000	.813	1.19	.41
17	1.063	.844	1.25	.43
18	1.125	.875	1.32	.46
19	1.188	.906	1.38	.48
20	1.250	.938	1.45	.50
21	1.313	.969	1.51	.52
22	1.375	1.000	1.57	.54
23	1.438	1.031	1.64	.57
24	1.500	1.063	1.71	.59
25	1.563	1.094	1.77	.61
26	1.625	1.125	1.84	.63
27	1.688	1.156	1.90	.66
28	1.750	1.188	1.97	.68
30	1.875	1.250	2.09	.72
31	1.938	1.281	2.16	.75
32	2.000	1.313	2.22	.77
34	2.125	1.375	2.35	.81
35	2.188	1.406	2.42	.83
36	2.250	1.438	2.48	.86
38	2.375	1.500	2.61	.90
40	2.500	1.563	2.74	.95
43	2.688	1.656	2.93	1.01
44	2.750	1.688	2.99	1.03
48	3.000	1.813	3.25	1.12
52	3.250	1.938	3.51	1.21
56	3.500	2.063	3.77	1.30
64	4.000	2.313	4.29	1.48
72	4.500	2.563	4.81	1.65
80	5.000	2.813	5.33	1.84
88	5.500	3.063	5.84	2.02
96	6.000	3.313	6.36	2.19

MATERIALS:

- (-) = 1010 STEEL, TEMPER 4 PER ASTM A109-85
FINISH - CADMIUM PLATING PER QQ-P-416, TYPE II, CLASS 2
- (D) = ALUMINUM ALLOY PER QQ-A-250/5
FINISH - HEAT TREAT PER MIL-H-6088 TO T42 CONDITION
- (DC) = ALUMINUM ALLOY PER QQ-A-250/5
FINISH - HEAT TREAT PER MIL-H-6088 TO T42 CONDITION
CHEMICAL FILM PER MIL-C-5541, CLASS 3, COLOR GOLD
- (C) = 302 CRES STEEL PER MIL-S-5059, ANNEALED OR 321 CRES STEEL PER AMS 5510, ANNEALED.
FINISH - CLEANED AND DESCALED IN ACCORDANCE WITH "ASTM A-380" AND PASSIVATED PER "QQ-P-35".

NOTE: ALUMINUM ALLOY CLAMPS MUST BE FORMED WITHIN ONE HOUR OF HEAT TREATMENT

EXAMPLES OF PART NUMBER:

- AN735-2 = STEEL CLAMP, .125 INSIDE DIA.
AN735D2 = ALUMINUM ALLOY CLAMP, .125 INSIDE DIA.
AN735DC2 = ALUMINUM ALLOY CLAMP WITH CHEMICAL FILM, .125 INSIDE DIA.
AN735C2 = CRES, STEEL CLAMP, .125 INSIDE DIA.