

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, stabilized or cancelled. SAE invites your written comments and suggestions.

REV.
C

SAE AS9209

RATIONALE

THIS DOCUMENT HAS BEEN DETERMINED TO CONTAIN BASIC AND STABLE TECHNOLOGY WHICH IS NOT DYNAMIC IN NATURE.

STABILIZED NOTICE

THIS DOCUMENT HAS BEEN DECLARED "STABILIZED" BY THE E-25 TECHNICAL COMMITTEE AND WILL NO LONGER BE SUBJECTED TO PERIODIC REVIEWS FOR CURRENCY. USERS ARE RESPONSIBLE FOR VERIFYING REFERENCES AND CONTINUED SUITABILITY OF TECHNICAL REQUIREMENTS. NEWER TECHNOLOGY MAY EXIST.

NOTICE

THE INITIAL SAE PUBLICATION OF THIS DOCUMENT WAS TAKEN DIRECTLY FROM U.S. MILITARY STANDARD MS9209, NOTICE 1. THIS SAE STANDARD RETAINS THE SAME PART NUMBERS ESTABLISHED BY THE ORIGINAL MILITARY DOCUMENT.

ANY REQUIREMENTS ASSOCIATED WITH QUALIFIED PRODUCTS LISTS (QPL) MAY CONTINUE TO BE MANDATORY FOR DOD CONTRACTS. REQUIREMENTS RELATING TO QPL'S HAVE NOT BEEN ADOPTED BY THE SAE FOR THIS STANDARD AND ARE NOT PART OF THIS SAE DOCUMENT.




FIGURE 1 - BOLT

SAE values your input. To provide feedback on this Technical Report, please visit <http://www.sae.org/technical/standards/AS9209C>

CUSTODIAN: E-25

PROCUREMENT SPECIFICATION: AS7459

SAE Aerospace
An SAE International Group

AEROSPACE STANDARD

BOLT, MACHINE - STEEL, DIFFUSED NICKEL-CADMIUM PLATED, DOUBLE HEXAGON EXTENDED WASHER HEAD, UNS K14675, 195 KSI MIN, .2500-28 UNJF-3A

SAE AS9209
SHEET 1 OF 3

REV.
C

Copyright 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Fax: 724-776-0790

Tel: +1 724-776-4970 (outside USA)
Email: CustomerService@sae.org

SAE WEB ADDRESS: <http://www.sae.org>

ISSUED 1999-12 REVISED 2011-08 STABILIZED 2012-01

TABLE 1 - PART NUMBERS AND DIMENSIONS

PART NO.	L	K	APPROX. MASS LB/100	PART NO.	L	K	APPROX. MASS LB/100.
MS9209-04	.365-.385	.079-.099	1.14	MS9209-34	2.740-2.760	1.940-2.000	3.85
MS9209-05	.428-.448	.079-.099	1.21	MS9209-35	2.865-2.885	2.065-2.125	4.00
MS9209-06	.490-.510	.079-.099	1.29	MS9209-36	2.990-3.010	2.190-2.250	4.14
MS9209-07	.552-.572	.079-.099	1.36	MS9209-37	3.115-3.135	2.315-2.375	4.29
MS9209-08	.615-.635	.079-.099	1.44	MS9209-38	3.240-3.260	2.440-2.500	4.43
MS9209-09	.678-.698	.079-.099	1.51	MS9209-39	3.365-3.385	2.565-2.625	4.58
MS9209-10	.740-.760	.079-.099	1.58	MS9209-40	3.490-3.510	2.690-2.750	4.72
MS9209-11	.802-.822	.079-.099	1.65	MS9209-41	3.615-3.635	2.815-2.875	4.85
MS9209-12	.865-.885	.125-.145	1.72	MS9209-42	3.740-3.760	2.940-3.000	4.99
MS9209-13	.928-.948	.128-.188	1.79	MS9209-43	3.865-3.885	3.065-3.125	5.13
MS9209-14	.990-1.010	.190-.250	1.86	MS9209-44	3.990-4.010	3.190-3.250	5.27
MS9209-15	1.052-1.072	.252-.312	1.93	MS9209-45	4.115-4.135	3.315-3.375	5.42
MS9209-16	1.115-1.135	.315-.375	2.00	MS9209-46	4.240-4.260	3.440-3.500	5.56
MS9209-17	1.178-1.198	.378-.438	2.08	MS9209-47	4.365-4.385	3.565-3.625	5.71
MS9209-18	1.240-1.260	.440-.500	2.15	MS9209-48	4.490-4.510	3.690-3.750	5.85
MS9209-19	1.302-1.322	.502-.562	2.22	MS9209-49	4.615-4.635	3.815-3.875	6.00
MS9209-20	1.365-1.385	.565-.625	2.29	MS9209-50	4.740-4.760	3.940-4.000	6.14
MS9209-21	1.428-1.448	.628-.688	2.36	MS9209-51	4.865-4.885	4.065-4.125	6.29
MS9209-22	1.490-1.510	.690-.750	2.43	MS9209-52	4.990-5.010	4.190-4.250	6.43
MS9209-23	1.552-1.572	.752-.812	2.50	MS9209-53	5.115-5.135	4.315-4.375	6.56
MS9209-24	1.615-1.635	.815-.875	2.57	MS9209-54	5.240-5.260	4.440-4.500	6.70
MS9209-25	1.678-1.698	.878-.938	2.64	MS9209-55	5.365-5.385	4.565-4.625	6.84
MS9209-26	1.740-1.760	.940-1.000	2.72	MS9209-56	5.490-5.510	4.690-4.750	6.99
MS9209-27	1.865-1.885	1.065-1.125	2.86	MS9209-57	5.615-5.635	4.815-4.875	7.13
MS9209-28	1.990-2.010	1.190-1.250	3.00	MS9209-58	5.740-5.760	4.940-5.000	7.28
MS9209-29	2.115-2.135	1.315-1.375	3.14	MS9209-59	5.865-5.885	5.065-5.125	7.42
MS9209-30	2.240-2.260	1.440-1.500	3.29	MS9209-60	5.990-6.010	5.190-5.250	7.57
MS9209-31	2.365-2.385	1.565-1.625	3.43				
MS9209-32	2.490-2.510	1.690-1.750	3.57				
MS9209-33	2.615-2.635	1.815-1.875	3.71				

NOTICE

THIS DOCUMENT REFERENCES A PART WHICH CONTAINS CADMIUM AS A PLATING MATERIAL. CONSULT LOCAL OFFICIALS IF YOU HAVE QUESTIONS CONCERNING CADMIUM'S USE.

NOTES:

- FOR PART NUMBERS MS9209-04 THRU MS9209-16 THE THREAD PD (DATUM -Z-) SHALL REPLACE DATUM -Y-.
- MATERIAL: LOW ALLOY STEEL AMS6304 (UNS K14675).
- PROCUREMENT SPECIFICATION: AS7459.
- HARDNESS: 42-46 HRC.
- FINISH: DIFFUSED NICKEL-CADMIUM PLATE AMS2416. DIMENSIONS ARE AFTER PLATING. CONTACT POINTS PERMISSIBLE. PD MAY BE REDUCED .0012 MAXIMUM BEFORE PLATING.

 An SAE International Group	AEROSPACE STANDARD	 SAE AS9209 SHEET 2 OF 3	REV. C
	BOLT, MACHINE - STEEL, DIFFUSED NICKEL-CADMIUM PLATED, DOUBLE HEXAGON EXTENDED WASHER HEAD, UNS K14675, 195 KSI MIN, .2500-28 UNJF-3A		