


REV. B	FEDERAL SUPPLY CLASS 5306	
	RATIONALE THIS DOCUMENT HAS BEEN REAFFIRMED TO COMPLY WITH THE SAE 5-YEAR REVIEW POLICY. THE INITIAL SAE PUBLICATION OF THIS DOCUMENT WAS TAKEN DIRECTLY FROM U.S. MILITARY STANDARD MS9455A, AMENDMENT 1. THIS SAE STANDARD RETAINS THE SAME PART NUMBERS ESTABLISHED BY THE ORIGINAL MILITARY DOCUMENT. ANY REQUIREMENTS ASSOCIATED WITH QUALIFIED PRODUCTS LISTS (QPL) MAY CONTINUE TO BE MANDATORY FOR DOD CONTRACTS. REQUIREMENTS RELATING TO QPL'S HAVE NOT BEEN ADOPTED BY THE SAE FOR THIS STANDARD AND ARE NOT PART OF THIS SAE DOCUMENT. WARNING THIS DOCUMENT INCLUDES CADMIUM AS A PLATING MATERIAL. THE USE OF CADMIUM HAS BEEN RESTRICTED AND/OR BANNED FOR USE IN MANY COUNTRIES DUE TO ENVIRONMENTAL AND HEALTH CONCERNS. THE USER SHOULD CONSULT WITH LOCAL OFFICIALS ON THE ENVIRONMENTAL AND HEALTH REGULATIONS REGARDING ITS USE.	
AS9455	SAENORM.COM : Click to view the full PDF of as9455.pdf	
CUSTODIAN: SAE E-25		THIRD ANGLE PROJECTION 
SAE Aerospace An SAE International Group	AEROSPACE STANDARD BOLT, MACHINE - STEEL, DIFFUSED NICKEL- CADMIUM PLATED, HEXAGON HEAD, UNS K14675, 195 KSI MIN, .4375-20 UNJF-3A	AS9455 SHEET 1 OF 4
		REV. B




TABLE 1 - PART NUMBERS AND DIMENSIONS

PART NO.	L	K	APPROX. MASS LB/100	PART NO.	L	K	APPROX. MASS LB/100
MS9455-04	.678 - .698	.105 - .125	5.78	MS9455-31	2.990 - 3.010	1.815 - 1.875	14.20
MS9455-05	.740 - .760	.105 - .125	6.01	MS9455-32	3.115 - 3.135	1.940 - 2.000	14.65
MS9455-06	.802 - .822	.105 - .125	6.24	MS9455-33	3.240 - 3.260	2.065 - 2.125	15.11
MS9455-07	.865 - .885	.105 - .125	6.47	MS9455-34	3.365 - 3.385	2.190 - 2.250	15.56
MS9455-08	.928 - .948	.105 - .125	6.69	MS9455-35	3.490 - 3.510	2.315 - 2.375	16.02
MS9455-09	.990 - 1.010	.105 - .125	6.92	MS9455-36	3.615 - 3.635	2.440 - 2.500	16.47
MS9455-10	1.052 - 1.072	.105 - .125	7.15	MS9455-37	3.740 - 3.760	2.565 - 2.625	16.93
MS9455-11	1.115 - 1.135	.105 - .125	7.37	MS9455-38	3.865 - 3.885	2.690 - 2.750	17.38
MS9455-12	1.178 - 1.198	.105 - .125	7.60	MS9455-39	3.990 - 4.010	2.815 - 2.875	17.84
MS9455-13	1.240 - 1.260	.125 - .145	7.83	MS9455-40	4.115 - 4.135	2.940 - 3.000	18.29
MS9455-14	1.302 - 1.322	.128 - .188	8.06	MS9455-41	4.240 - 4.260	3.065 - 3.125	18.74
MS9455-15	1.365 - 1.385	.190 - .250	8.28	MS9455-42	4.365 - 4.385	3.190 - 3.250	19.20
MS9455-16	1.428 - 1.448	.252 - .312	8.51	MS9455-43	4.490 - 4.510	3.315 - 3.375	19.65
MS9455-17	1.490 - 1.510	.315 - .375	8.74	MS9455-44	4.615 - 4.635	3.440 - 3.500	20.11
MS9455-18	1.552 - 1.572	.378 - .438	8.97	MS9455-45	4.740 - 4.760	3.565 - 3.625	20.56
MS9455-19	1.615 - 1.635	.440 - .500	9.19	MS9455-46	4.865 - 4.885	3.690 - 3.750	21.02
MS9455-20	1.678 - 1.698	.502 - .562	9.42	MS9455-47	4.990 - 5.010	3.815 - 3.875	21.47
MS9455-21	1.740 - 1.760	.565 - .625	9.65	MS9455-48	5.115 - 5.135	3.940 - 4.000	21.93
MS9455-22	1.865 - 1.885	.690 - .750	10.10	MS9455-49	5.240 - 5.260	4.065 - 4.125	22.38
MS9455-23	1.990 - 2.010	.815 - .875	10.56	MS9455-50	5.365 - 5.385	4.190 - 4.250	22.84
MS9455-24	2.115 - 2.135	.940 - 1.000	11.01	MS9455-51	5.490 - 5.510	4.315 - 4.375	23.29
MS9455-25	2.240 - 2.260	1.065 - 1.125	11.47	MS9455-52	5.615 - 5.635	4.440 - 4.500	23.75
MS9455-26	2.365 - 2.385	1.190 - 1.250	11.92	MS9455-53	5.740 - 5.760	4.565 - 4.625	24.20
MS9455-27	2.490 - 2.510	1.315 - 1.375	12.38	MS9455-54	5.865 - 5.885	4.690 - 4.750	24.66
MS9455-28	2.615 - 2.635	1.440 - 1.500	12.83	MS9455-55	5.990 - 6.010	4.815 - 4.875	25.11
MS9455-29	2.740 - 2.760	1.565 - 1.625	13.29				
MS9455-30	2.865 - 2.885	1.690 - 1.750	13.74				

NOTES:

1. MATERIAL: LOW ALLOY STEEL AMS 6304 (UNS K14675).
2. PROCUREMENT SPECIFICATION: AS7455.
3. HARDNESS: 42-46 HRC.
4. FINISH: DIFFUSED NICKEL-CADMIUM PLATE AMS 2416. DIMENSIONS ARE AFTER PLATING. CONTACT POINTS PERMISSIBLE. PD MAY BE REDUCED .0012 MAXIMUM BEFORE PLATING.
5. MAGNETIC PARTICLE INSPECTION PER ASTM E 1444 BEFORE PLATING.
6. INCOMPLETE THREADS NOT TO ENTER FILLET.
7. SURFACE TEXTURE: SYMBOLS PER ASME Y14.36M. REQUIREMENTS PER ASME B46.1. UNLESS OTHERWISE SPECIFIED, SURFACES TO BE 125 MICROINCHES Ra.
8. BREAK SHARP EDGES .003-.015, UNLESS OTHERWISE SPECIFIED.
9. DIMENSIONING AND TOLERANCING PER ANSI Y14.5M-1982 (ASME PUBLICATION).