

SURFACE VEHICLE RECOMMENDED PRACTICE

SAE J1691

ISSUED
APR97

Issued

1997-04

Plastic Motor Vehicle Safety Glazing—Tolerances and Fabrication Details

1. Scope—This SAE Recommended Practice is intended to cover plastic safety glazing for use in motor vehicles and motor vehicle equipment. Nominal specifications for thickness, flatness, curvature, size, and fabrication details are presented principally for the guidance of body engineers and designers. For additional information on plastic safety glazing materials for use in motor vehicles and motor vehicle equipment, please see SAE J674.

2. References

2.1 Applicable Publication—The following publication forms a part of this specification to the extent specified herein. Unless otherwise indicated, the latest issue of SAE publications shall apply.

2.1.1 SAE PUBLICATION—Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

SAE J674—Safety Glazing Materials—Motor Vehicles

2.2 Related Publications—The following publications are provided for information purposes only and are not a required part of this document.

2.2.1 SAE PUBLICATION—Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

SAE J673—Automotive Safety Glazing

2.2.2 FMVSS PUBLICATION—Available from the Superintendent of Documents, U. S. Government Printing Office, Mail Stop: SSOP, Washington, DC 20402-9320.

FMVSS 205—Glazing Materials

3. Sizes—There are no standard sizes applicable to plastic safety glazing for use in motor vehicles and motor vehicle equipment. The feasibility of proposed plastic safety glazing sizes developed by the motor vehicle/motor vehicle equipment manufacturer must be determined by conference with the plastic glazing fabricator.

The various types of plastic safety glazing (flat or curved) are as follows: injection molded, extruded (formed), and cell cast.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

QUESTIONS REGARDING THIS DOCUMENT: (412) 772-8512 FAX: (412) 776-0243
TO PLACE A DOCUMENT ORDER: (412) 776-4970 FAX: (412) 776-0790

4. Typical Commercial Tolerance Information

- 4.1 Thickness**—Commercially available flat or curved plastic safety glazing has thickness tolerance as follows in Table 1:

Table 1—THICKNESSES⁽¹⁾

Type of Plastic Safety Glazing	Typical Nominal Thickness
Injection Molded and Extruded	4.00, 5.00, and 6.00 ($\pm 5\%$ of total thickness) mm
	0.157, 0.197, and 0.236 ($\pm 5\%$ of total thickness) inches
Cell Cast	4.00, 5.00, and 6.00 (+0.406/−0.762 to +0.508/−1.02) mm
	0.157, 0.197, and 0.236 (+0.016/−0.03 to +0.02/−0.04) in

1. NOTE—Other plastic safety glazing thicknesses may be acceptable for use in motor vehicles and motor vehicle equipment provided they meet the requirements of all applicable laws, regulations, codes, and practices in effect.

- 4.2 Flatness**—Flat safety plastic glazing of the types noted may have 0.8 mm (0.03 in) maximum total bow per 305 mm (12 in length), and each part may have a maximum overall bow, in millimeters, of 0.0026 times the length of the part.

- 4.3 Curvature**—Dimensional tolerances on the physical dimensions of curved injection molded, extruded (formed), or cell cast plastic automotive safety glazing parts shall be specified as follows, with reference to numeric design data or to a master die model derived from numeric data supplied by the automotive manufacturer.

- a. Size—Maximum size (plus zero) with specified minimum size. Allowances must be made for the thermal expansion and contraction of the material based upon design and installation. The Coefficient of Thermal Expansion for polycarbonate and acrylic are shown as examples in Table 2.

Table 2—COEFFICIENT OF THERMAL EXPANSION FOR TYPICAL PLASTIC GLAZING MATERIALS

Type of Plastic Safety Glazing Material	Coefficient of Thermal Expansion
Polycarbonate	6.75×10^{-5} (m/m/°C), 3.75×10^{-5} (in/in/°F)
Acrylic	7.4×10^{-5} (m/m/°C), 4.1×10^{-5} (in/in/°F)

- b. Thickness—Nominal thickness, with acceptable commercial ranges above and below nominal.
- c. Contour—Peripheral or edge contour may be specified in terms of maximum departure from the peripheral face of the desired surface. Central area surface contour may be specified in terms of permissible deviations of curvature from the designed contour. For example, this contour may be measured from the vertical centerline chord of the plastic, taken at the point of maximum designed depth of curvature.

NOTE—Manufacturing tolerances on size and contour will vary with design and should be established by conference. Designs for complex curved parts should recognize and accommodate necessary tolerances on size and shape.

5. Fabrication Details

- 5.1** Curved plastic safety glazing parts are generally checked for size and curvature on a male checking gauge made to receive the desired surface of the plastic. The male checking gauge should be accurate, rigid, and permanent. Size is checked using maximum and minimum lines, stops, or notches on the gauge.
- 5.2** Peripheral or edge contour is usually checked by inserting a thickness feeler gauge (where possible) between the face of the checking ledge and the plastic. The width of the face of the checking ledge can vary with design and should be established by conference.
- 5.3** The central area of the checking gauge is undercut, with a spring pin or other means of checking the surface contour at the specified area.
- 5.4** Size tolerances for curved injection molded, extruded, or cast plastic glazing are affected by pattern and degree of curvature and should be checked by the manufacturer.
- 5.5 Mark Off (Extruded or Cell Cast)**—Mark-off for thermoformed cast or extruded sheet may extend to 13 mm (0.5 in) maximum from the edge of the plastic depending on the size and complexity of the curved part, unless otherwise specified.
- 5.6 Drilled Holes (Extruded or Cell Cast)**—The dimensions and tolerances for the size and location of drilled holes will vary with design and plastic thickness and should be established by conference.
- 5.7 Edges**—The edges should be finished with regard to the design and engineering of the motor vehicle, location of the glazing and in conjunction with regulatory standards as well as the plastic glazing manufacturer's recommended practices.
- 5.8** Injection-molded edges do not require finishing unless specified by the automotive manufacturer or regulatory requirements.
- 5.9 Markings**—Markings are to be in accordance with current government regulations. Location of these markings must be visible for identification after installation. Any other special identifying marks required must be specified and located on the drawing and must be apart from the plastic manufacturer's distinctive trademark or other markings required by law, ordinance, or regulation.

PREPARED BY THE SAE GLAZING MATERIALS STANDARDS COMMITTEE