



SURFACE VEHICLE STANDARD

J191

SEP2014

Issued 1970-08
Stabilized 2014-09

Superseding J191 JUN2003

Power Steering Pressure Hose - Low Volumetric Expansion Type

RATIONALE

The technical report covers technology, products, or processes which are mature and not likely to change in the foreseeable future.

STABILIZED NOTICE

This document has been declared "Stabilized" by the SAE Automotive Brake and Steering Hose Standards Committee and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAENORM.COM : Click to view the full PDF of J191-201409

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2014 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

SAE values your input. To provide feedback
on this Technical Report, please visit
http://www.sae.org/technical/standards/J191_201409

Foreword—This document represents the minimum quality recognized by original equipment manufacturers and hose suppliers as essential for satisfactory and safe operation by the hose itself and other coating parts of the power steering system. The original equipment manufacturer may, at his option, add or alter tests through OEM specifications.

1. **Scope**—This SAE Standard covers hose fabricated from fabric braid and synthetic rubber, assembled with end fittings for use in automotive power steering applications at pressures as indicated in Table 1B, as flexible connections within the temperature range of -40°C (-40°F) to 121°C (250°F) average, 135°C (275°F) maximum peaks.

These hoses are intended for use in applications where reduction in amplitude of pump pressure pulsations is not required.

2. References

- 2.1 **Applicable Publications**—The following publications form a part of the specification to the extent specified herein.

- 2.1.1 **ASTM PUBLICATIONS**—Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM D 380—Methods of Testing Rubber Hose

ASTM D 413—Tests for Adhesion of Vulcanized Rubber (Friction Test)

3. **Hose Construction**—The construction of this hose embodies a smooth bore inner tube of suitable synthetic rubber material, reinforced with two plies of braided fabric and covered with a synthetic rubber outer cover.
4. **Dimensions**—Hose must be within the tolerances shown in Table 1B. In addition, the concentricity based on full indicator reading between the inside bore and the outer surface of the hose shall not exceed 0.076 cm (0.030 in).
5. **Test Procedures**—Procedures described in ASTM D 380 shall be followed wherever applicable.

TABLE 1A—HOSE DIMENSIONS (METRIC)

Nominal ID, cm	Nominal OD, cm	ID Tolerance, cm	OD Tolerance, cm	Working Pressure, max, MPa	Proof Pressure, MPa	Burst Strength, min, MPa	Tensile Strength, min, N
0.635	1.429	0.699/0.61	1.5/1.4	8.96	13.8	41.4	2001.7

TABLE 1B—HOSE DIMENSIONS (ENGLISH)

Nominal ID, in	Nominal OD, in	ID Tolerance, in	OD Tolerance, in	Working Pressure, max, psi	Proof Pressure, psi	Burst Strength, min, psi	Tensile Strength, min, lb
1/4	9/16	0.275/0.240	0.592/0.552	1300	2000	6000	450

- 6. Qualification Tests**—To qualify hose under this document, all of the requirements shown in Section 9 must be met.
- 7. Inspection Tests**—Production shipments or lots of qualified hose shall be tested in accordance with Table 2 and shall conform to the applicable test requirements, but the user may test hose or hose assemblies from any or all such production shipments or lots to all the test requirements. Fourteen sample hose assemblies, selected at random, as listed in Table 2, are required to conduct a complete test. In the event of a failure, the test or tests that have failed shall be retested using twice the number of samples indicated in Table 2. Failure of any of the retested samples shall be cause for rejection of the entire lot.

TABLE 2—INSPECTION TESTS

Test	Samples Required
1. Length Change (9.7) followed by Bursting Strength (9.5)	3
2. Tensile (9.2)	3
3. Adhesion (9.4)	1
4. Low Temperature Flexibility (9.3)	1
5. Impulse (9.1)	6

- 8. Frequency of Testing for Inspection**—All inspection tests except impulse shall be performed on either a bulk hose lot or a coupled hose lot basis or tests may be split between a bulk hose lot and a coupled hose lot.

A coupled hose lot shall not exceed 10 000 hose assemblies and a bulk hose lot shall not exceed 6096 m (20 000 ft) of bulk hose. The lot size for impulse testing shall not exceed 30 480 m (100 000 ft) of bulk hose.

9. Test Requirements

9.1 Impulse Test

9.1.1 TEST CONDITIONS

- Oil Temperature— $135^{\circ}\text{C} \pm 2^{\circ}\text{C}$ ($275^{\circ}\text{F} \pm 5^{\circ}\text{F}$)
- Ambient Temperature— $104^{\circ}\text{C} \pm 11^{\circ}\text{C}$ ($220^{\circ}\text{F} \pm 20^{\circ}\text{F}$)
- Cycle Rate—30 to 40 per minute.
- Cycle Data—Pressure rise time, $0.20\text{ s} \pm 0.10\text{ s}$. High pressure hold time, $0.65\text{ s} \pm 0.20\text{ s}$. Pressure drop time, $0.20\text{ s} \pm 0.10\text{ s}$.
- Pressure Variation—0 to 0.69 MPa (0 to 100 psi) to maximum working pressure listed in Table 1B.

- 9.1.2 **HYDRAULIC FLUID AND TEST FIXTURE**—As specified by the original equipment manufacturer.
- 9.1.3 **CYCLE LIFE**—Samples submitted to this test shall exceed 100 000 cycles for inspection acceptance and 225 000 cycles for qualification testing, without failure.
- 9.2 **Tensile Test**—When tested in accordance with ASTM D 380, hose assemblies shall withstand a minimum tensile load as specified in Table 1 without the fittings pulling off or rupture of the hose.
- 9.3 **Low Temperature Flexibility**—Samples shall be subjected to a temperature of $-40\text{ }^{\circ}\text{C} \pm 1\text{ }^{\circ}\text{C}$ ($-40\text{ }^{\circ}\text{F} \pm 2\text{ }^{\circ}\text{F}$) for a period of 24 h, after which the hose shall be flexed in the cold chamber through 180 degrees from the centerline around a mandrel whose diameter is eight times the nominal hose OD. Flexing shall be accomplished within 4 s. Hose shall not fracture or show any cracks, checks, or breaks in the tube or cover.
- 9.4 **Adhesion Test**—When tested in accordance with ASTM D 413, a pull of not less than 44.48 N (10 lb) shall be required to separate a 2.54 cm (1 in) wide ring section of the bond between any adjacent layers of the hose.
- 9.5 **Bursting Strength**—Samples shall meet the minimum bursting strength requirements shown in Table 1B.
- 9.6 **Ozone Resistance**—The outer cover of the hose shall show no cracking when examining the cover of the hose under 7X magnification, ignoring the areas immediately adjacent to or within the area covered by the binding.
- Bend the hose around a cylinder, the diameter of which shall be seven times the nominal outside diameter of the hose, and bind the ends. The cylinder and binding shall be made of metal or materials that prevent the consumption of ozone. If the hose collapses when bent around the cylinder, provide for internal support of the hose.
- Condition the hose, on the cylinder, for $24.0\text{ h} \pm 0.5\text{ h}$ at room temperature, and then place it in an exposure chamber containing air mixed with ozone in the proportion of 50 pphm $\pm$ 5 ozone in air by volume, for 70 to 72 h. Ambient air temperature in chamber during test shall be $40\text{ }^{\circ}\text{C} \pm 3\text{ }^{\circ}\text{C}$ ($104\text{ }^{\circ}\text{F} \pm 5\text{ }^{\circ}\text{F}$). Examine the cover of the hose for cracks under 7X magnification, ignoring the areas immediately adjacent to or within the area covered by the binding.
- 9.7 **Length Change**—Hose shall not change in length more than +2%, –4% when pressure is increased from 0 MPa (0 psi) to the maximum working pressure shown in Table 1B.
- 9.8 **Tensile Strength and Elongation**
- Original Tensile Strength of Cover—6.9 MPa (1000 psi) min
 - Original Tensile Strength of Tube—6.9 MPa (1000 psi) min
 - Original Elongation of Cover—175% min
 - Original Elongation of Tube—150% min
- 9.9 **Dry Heat Resistance**—After oven aging for 70 h at a temperature of $100\text{ }^{\circ}\text{C}$ ($212\text{ }^{\circ}\text{F}$), the reduction in tensile strength and elongation of specimens taken from tube and cover material shall not exceed the following values:
- Original Tensile Strength—20%
 - Original Elongation—50%