

SAE J525 MAY86

**Welded and Cold
Drawn Low Carbon
Steel Tubing
Annealed for Bending
and Flaring**

**SAE Standard
Reaffirmed May 1986**

SAENORM.COM : Click to view the full PDF of J525-198605

S. A. E.
LIBRARY

SAENORM.COM : Click to view the full PDF of j525_198605

No part of this publication may be reproduced in any form, in an electronic retrieval system or otherwise, without the prior written permission of the publisher.

Copyright 1986 Society of Automotive Engineers, Inc.

**PARTS AND
COMPONENTS
STANDARD**

Submitted for recognition as an American National Standard

SAE J525

Issued April 1958
Reaffirmed May 1986

Reaffirms J525 JAN80

WELDED AND COLD DRAWN LOW CARBON STEEL TUBING ANNEALED FOR BENDING AND FLARING

1. **SCOPE:** This standard covers cold worked and annealed electric resistance welded single wall low carbon steel pressure tubing intended for use as hydraulic lines and in other applications requiring tubing of a quality suitable for flaring and bending.
2. **MANUFACTURE:** The tubing shall be made from a single strip of steel shaped in to a tubular form, the edges of which are joined and sealed by electric resistance welding. After forming and welding, the tubing shall be normalized and subjected to a cold working operation that shall result in a 15% minimum reduction in cross sectional area, of which at least 8% shall consist of a reduction in wall thickness. Subsequent to cold working, the tubing shall be annealed in such a manner as to produce a finished product which will meet all requirements of this standard. Tubing that has been pickled to remove scale shall be suitably treated to eliminate any embrittlement induced by the pickling process.
3. **DIMENSIONS AND TOLERANCES:** The tolerances applicable to tubing outside diameter, inside diameter, and wall thickness are shown in Table 1. Tubing shall be subject to any two of the tolerances specified, as designated by the purchaser.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

4. **QUALITY:** Lengths of finished tubing shall be reasonably straight and have smooth ends free from burrs. Tubing shall be free from scale and injurious defects and have a workmanlike finish. Surface imperfections such as handling marks, die marks, or shallow pits shall not be considered injurious defects provided the imperfections are within the tolerances specified for diameter and wall thickness. The removal of such surface imperfections is not required. There shall be no dimensional indications of the presence of the weld.

The inside of tubing shall be clean and free from any contamination that cannot be readily removed by cleaning agents normally used in manufacturing.

5. **MATERIAL:** Tubing shall be made from low carbon steel conforming to the following chemical composition.

Element	Cast or Heat Analysis ^a % by Weight
Carbon	0.18 max
Manganese	0.30-0.60
Phosphorus	0.040 max
Sulfur	0.050 max

^aCheck analysis tolerance shall be as specified in SAE J409, Table 3.

6. **MECHANICAL PROPERTIES:** The finished tubing shall have mechanical properties as tabulated below:

Yield Strength, min	25,000 psi (170 MPa)
Ultimate Strength, min	45,000 psi (310 MPa)
Elongation in 2 in (50 mm), min	35% ^a
Hardness (Rockwell B scale), max	65 ^b

^aFor tubing having nominal outside diameter of 0.375 in (9.5 mm) or less, and/or wall thicknesses of 0.035 in (0.9 mm) or less, a minimum elongation of 25% is permissible.

^bThe hardness test shall not be required on tubing with a nominal wall thickness of less than 0.065 in (1.65 mm). Such tubing shall meet all other mechanical properties and performance requirements.

7. PERFORMANCE REQUIREMENTS: The finished tubing shall satisfactorily meet the following performance tests. Test specimens shall be taken from tubing which has not been subjected to cold working after the anneal of the finished sized tubing.

- 7.1 Flattening Test: A section approximately 3 in (75 mm) in length, cut from the finished tubing, shall not crack or show any flaws when flattened between parallel plates to a distance equal to three times the wall thickness of the section under test. Superficial ruptures resulting from minor surface imperfections shall not be considered cause for rejection.
- 7.2 Reverse Flattening Test: A test specimen shall be taken from every shipment or every 1500 ft (460 m), whichever is smaller, of finished tubing and split longitudinally 90 deg on each side of the weld. The section containing the weld shall be opened and flattened with the weld at the point of maximum bend. There shall be no evidence of cracks or lack of penetration or overlaps resulting from flash removal in the weld.

Refer to ASTM A 370, Methods and Definitions for Mechanical Testing of Steel Products, paragraph T5(B), reverse flattening test.

- 7.3 Expansion Test: A test specimen shall be taken from every shipment or every 1500 ft (460 m), whichever is smaller, of finished tubing and subjected to expansion over a hardened tapered plug having a slope of 0.1:1.0 until the outside diameter has been expanded 25% without evidence of cracking or flaws.
- 7.4 Pressure Proof Test: Unless otherwise specified, tubing supplied under this standard shall have been tested hydrostatically, with no evidence of failure, at a pressure which will subject the material to a yield stress of 20,000 psi (140 MPa). Test pressures shall be as determined by Barlow's formula for thin hollow cylinders under tension:

$$P = \frac{2TS}{D}$$

where: D = outside diameter of tubing, in (mm)
P = hydrostatic pressure, psi (MPa)
S = allowable unit stress of material = 20,000 psi (140 MPa)
T = minimum wall thickness of tubing, in (mm)

No tube shall be tested beyond a hydrostatic pressure of 5000 psi (35 MPa) unless so specified.

- 7.5 Nondestructive Electric Test: In lieu of the hydrostatic test, where mutually agreed upon by the purchaser and manufacturer, all tubing shall be tested by passing it through an electric eddy current tester which is capable of detecting defects that would prevent the tubing from passing the hydrostatic pressure proof test.
8. CORROSION PROTECTION: The inside and outside of the finished tubing shall be protected against corrosion during shipment and normal storage. If a corrosion preventive compound is applied, it shall be such that after normal storage periods it can readily be removed by cleaning agents normally used in manufacturing.

TABLE 1--TUBING OUTSIDE DIAMETER AND WALL THICKNESS TOLERANCE

Nominal Tubing OD ^{a, b}		Tolerance + _				Wall Thickness (%)
in	mm	OD		ID		
		in	mm	in	mm	
Up to 0.38	Up to 9.5	0.002	0.05	0.002	0.05	15
Over 0.38 to 0.63 inclusive	Over 9.5 to 15.9 inclusive	0.0025	0.06	0.0025	0.06	10
Over 0.63 to 2.00 inclusive	Over 15.9 to 50.8 inclusive	0.003	0.08	0.003	0.08	10
Over 2.00 to 2.50 inclusive	Over 50.8 to 63.5 inclusive	0.004	0.10	0.004	0.10	10
Over 2.50 to 3.00 inclusive	Over 63.5 to 76.2 inclusive	0.005	0.13	0.005	0.13	10
Over 3.00 to 4.00 inclusive	Over 76.2 to 101.6 inclusive	0.006	0.15	0.006	0.15	10

^aThe actual outside diameter shall be the average of the maximum and minimum outside diameters as determined at any one cross section through the tubing.

^bRefer to SAE J514 for nominal tubing outside diameters to be used in conjunction with standard hydraulic tube fittings.

RATIONALE:

Not applicable.

RELATIONSHIP OF SAE STANDARD TO ISO STANDARD:

Not applicable.

REFERENCE SECTION:

SAE J1409, Air Brake Valves Test Procedure

ASTM A370, Methods and Definitions for Mechanical Testing of Steel Products

APPLICATION:

This standard covers cold worked and annealed electric resistance welded single wall low carbon steel pressure tubing intended for use as hydraulic lines and in other applications requiring tubing of a quality suitable for flaring and bending.

COMMITTEE COMPOSITION:

DEVELOPED BY THE SAE AUTOMOTIVE AND HYDRAULIC TUBING SUBCOMMITTEE:

Subcommittee currently being reorganized.

SPONSORED BY THE SAE FLUID CONDUCTORS AND CONNECTORS TECHNICAL COMMITTEE, OF THE MATERIALS, PROCESSES, AND PARTS DIVISION:

R. J. Lobmeyer, Deere & Co., Waterloo, IA - Chairman
G. B. Apgar, Rilsan Industrial, Inc., Birdsboro, PA
D. M. Bauer, Aeroquip Corp., Van Wert, OH
H. D. Berns, Deere & Co., Moline, IL
D. G. Burge, Parker-Hannifin Corp., Ostego, MI
H. M. Cooke, Stratoflex, Inc., Fort Worth, TX
W. P. Coyne, USA Belvoir R & D Center, Ft. Belvoir, VA
R. A. Crowder, Bundy Corporation, Warren, MI
W. E. Currie, Parker-Hannifin Corp., Wickliffe, OH
V. T. Czebatol, ITT Higbie Mfg. Co., Rochester, MI
F. E. Flake, Clark Michigan Company, Benton Harbor, MI
R. C. Harrison, United Technologies Corp., Ft. Wayne, IN
W. A. Hertel, Parker-Hannifin Corp., Cleveland, OH
R. E. Holmgren, Dayco Corp., Libertyville, IL
H. Jenkins, Defense Logistics Agency, Columbus, OH
B. Keister, Eaton Corp., Mantua, OH
O. Linger, Kendavis Industries, Green Camp, OH
R. D. Mayne, Navistar Int'l. Corp., Ft. Wayne, IN
H. B. Newman, Caterpillar Tractor Company, Peoria, IL
S. T. Nguyen, Belvoir R & D Center, Ft. Belvoir, VA
J. Penninger, Kendavis Industries Int'l., Inc., Fort Worth, TX
P. E. Robinson, Parker-Hannifin Corp., Cleveland, OH
R. K. Schantz, Clark Michigan Company, Benton Harbor, MI
R. F. Sievert, Arrowline Products, Inc., Rockford, IL