



SURFACE VEHICLE INFORMATION REPORT

J947™

JUN2023

Issued 1966-06
Reaffirmed 2014-01
Stabilized 2023-06

Superseding J947 JAN2014

Glossary of Fiberboard Terminology

RATIONALE

This document has been determined to contain basic and stable technology which is not dynamic in nature.

STABILIZED NOTICE

This document has been declared "STABILIZED" by SAE Textile and Flexible Plastics Committee and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAENORM.COM : Click to view the full PDF of J947_202306

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2023 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
https://www.sae.org/standards/content/J947_202306/

1. SCOPE

This information report presents the terminology and definitions as used in the fiberboard industry.

2. REFERENCES

There are no referenced publications specified herein.

3. DEFINITIONS

See Scope.

3.1 Fiberboard

3.1.1 Description

A broad general term for fibrous structures produced on any of the several types of fiber forming machines. The primary composition of these boards is normally refined cellulosic or matted wood fibers which may or may not be supplemented by the use of synthetic materials or chemical additives. The manufacture of fiberboards normally involves the formation of a wet web of suspended fibers, which is subsequently pressed, dried, and often calendared or laminated to develop desired end use properties.

3.1.2 Physical/Mechanical Properties

Except for the characteristic fibrous structure, the physical properties may vary over a wide range. The term fiberboard is normally limited to thicknesses of 0.23 mm (0.009 in) or above.

3.1.3 Applications

The normal uses for this material include nearly all automotive applications where fibrous board structures are specified.

SAENORM.COM : Click to view the full PDF of J947 JUN202306

3.2 Fiberboards Classified by Manufacture

3.2.1 Hardboard

3.2.1.1 Description

A generic term for a sheet manufactured primarily from interfelted lignocellulosic fibers (usually wood) consolidated under heat and pressure in a hot press to a density of 880 to 1041 kg/m³ (55 to 65 lb/ft³) (specific gravity 0.9 to 1.0) or greater, and to which other materials may have been added during manufacture to improve certain properties.

3.2.1.2 Physical/Mechanical Properties

This material is generally a stiff grade of fiberboard with isotropic physical properties.

3.2.1.3 Applications

The normal uses for this material include nearly all automotive applications where fibrous board structures are specified.

3.2.2 Paperboard

3.2.2.1 Description

A generic term for a sheet manufactured primarily from cellulosic fibers produced by conventional pulping and paper making process and equipment.

3.2.2.2 Physical/Mechanical Properties

Except for the characteristic fibrous structure, the physical properties may vary over a wide range. The paperboards are anisotropic with the board machine direction having greater strength and dimensional stability.

3.2.2.3 Applications

The normal uses for this material include nearly all automotive applications where fibrous board structures are specified.

3.2.3 Chipboard

3.2.3.1 Description

A general term describing a type of fiberboard produced primarily from mixed grades of waste paper and most often produced on a cylinder machine. The final product may be sold as either a single ply or laminated board.

3.2.3.2 Physical/Mechanical Properties

The material is usually characterized by low density and gray color and is used where strength and quality are not required. The final product may be modified by the addition of nonfibrous components to impart water resistance or other special properties. The normal range of thickness is from about 0.23 to 1.14 mm (0.009 to 0.045 in) for single ply and 1.27 to 5.08 mm (0.050 to over 0.200 in) for laminated constructions.

3.2.3.3 Applications

Used in applications where appearance and ultimate strength are not important. Typical uses include visor cores, trim panel subfoundations, and some gasket applications.

3.2.4 Laminated Board

3.2.4.1 Description

A general term describing a board comprised of two or more single plies of board, paper, or other sheet materials in any combination, firmly adhered to each other by means of an adhesive between the plies. The adhesion and cohesion of the entire finished structure are such that it will function as a single unit.

3.2.4.2 Physical/Mechanical Properties

Except for the multiple structure, the physical characteristics of laminated boards vary over a wide range of properties. Because of the general nature of the term, there are few typical physical characteristics.

3.2.4.3 Applications

Typical uses include head liners, trunk liners, glove boxes, and door panels.

3.2.5 Wet Machine Board (Homogeneous)

3.2.5.1 Description

This material is produced on a one cylinder wet machine. It is manufactured by the building up on a roll of a number of wet plies of paper stock (refined cellulose fibers) from a continuous web. The wet plies adhere mechanically to one another in the wet state and, when the desired thickness of board has been reached, the wet stock (approximately 40% solids) is removed from the make roll as a sheet. It is then pressed, dried, and calendered to the desired finished thickness. The pressing and drying operations develop strong fiber-to-fiber chemical and mechanical bonds within the plies and between the ply interfaces.

3.2.5.2 Physical/Mechanical Properties

This board is characterized by high density stiffness and strength. This material is commonly produced in calipers ranging from a minimum of 1.27 mm (0.050 or 0.060 in) up to a thickness of 25.4 mm (0.500 to 1.0 in) for various applications. This material frequently contains nonfibrous components such as resins or asphalt to develop water resistance, formability, or other special properties.

3.2.5.3 Applications

Typical uses include tacking strips and dash insulators.

3.2.6 Kraft Paper

3.2.6.1 Description

Kraft is the generic name for paper of high strength which identifies the sulfate chemical pulping process from which the paper is made. The sulfate pulping process involves cooking wood fibers in an alkaline medium to produce strong, cellulosic fiber which is normally converted to paper on a Fourdrinier paper machine.

3.2.6.2 Physical/Mechanical Properties

The term paper is normally restricted to materials 0.23 mm (0.009 in) or under in caliper and usually less than 127 g/m² (26 lb/1000 ft²). The kraft paper is characterized by a reddish-brown color in the unbleached state, but may be bleached to a very high brightness white for some applications. This material normally has high strength and is relatively dense.

3.2.6.3 Applications

Uses include wire wrapping, braided insulators, liner for laminated fiberboards, and water shields.