

A Product of the
Cooperative Engineering Program

SAE J997 JUN88

**Spark Arrester Test
Carbon**

**SAE Standard
Revised June 1988**

SAENORM.COM : Click to view the full PDF of 1997-098806

**S. A. E.
LIBRARY**

**Submitted for Recognition as
an American National Standard**

SAENORM.COM : Click to view the full PDF of j997_198806

No part of this publication may be reproduced in any form,
in an electronic retrieval system or otherwise, without the
prior written permission of the publisher.

Copyright 1988 Society of Automotive Engineers, Inc.

Ø SPARK ARRESTER TEST CARBON

1. PURPOSE:

The purpose of this SAE Standard is to establish specifications for test carbon to be used when performing the tests described in SAE J335, J342, and J350.

2. SCOPE:

This SAE Standard establishes physical properties required of SAE Coarse Test Carbon and SAE Fine Test Carbon, and establishes test methods to ensure that these requirements are met.

3. TEST CARBON REQUIREMENTS:

3.1 Type: The test carbon shall be petroleum coke.

3.2 Form: The test carbon shall be granular in form.

3.3 Size: The size distribution of particles of test carbon shall be as follows:

3.3.1 Fine Carbon:

Pass through U.S. Standard No. 16 Sieve: 100% by mass
Retained on U.S. Standard No. 20 Sieve: 70% by mass
Retained on U.S. Standard No. 30 Sieve: 30% by mass

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

3.3.2 Coarse Carbon:

Pass through U.S. Standard No. 8 Sieve: 100% by mass
Retained on U.S. Standard No. 12 Sieve: 60% by mass
Retained on U.S. Standard No. 16 Sieve: 40% by mass

3.3.3 Mixing: Before use, mix screened fractions by pouring from one container to another at least five times.

3.4 Activity: The test carbon shall conform to the commercial definition of "activated carbon."

3.5 Apparent Density: 0.5 - 0.6 g/cm³ when vibrated to minimum volume (See paragraph 4.3).

3.6 Strength: 75-90% (See paragraph 4.4).

4. TEST METHODS:

4.1 Apparent Density:

4.1.1 Principle: The apparent density is the mass of a unit volume of the sample, including the pores and voids between the particles. It is obtained by measuring the volume of a weighed sample in a graduate.

4.1.2 Apparatus:

4.1.2.1 A balance of 100 g capacity, accurate to 0.01 g.

4.1.2.2 A 100 cm³ graduated cylinder, accurate to 0.01 cm³.

4.1.2.3 A vibrating table, such as shown in Fig. 2. The table shown in Fig. 2 is a 3/4 in (19 mm) air vibrator fastened to the vibrating table which is supported on rubber belting. Any shaker which provides adequate packing of the sample may be used.

4.1.3 Procedure:

4.1.3.1 Dry 50 g of the sample for at least 6 h at 150°F.

4.1.3.2 Loosely support the graduated cylinder on the vibrating table and start the vibrator.

4.1.3.3 Weigh out a 39.5 - 40.5 g portion of the dried sample.

4.1.3.4 Pour the sample slowly into the graduated cylinder. The vibrator shall be in motion all during the time the sample is being poured into the graduate, and shall not be turned off until 60 s after the last of the sample enters the graduated cylinder.

4.1.4 Calculation:

$$\text{Apparent Density} = \frac{\text{mass of dried sample, g}}{\text{volume of sample, cm}}$$

4.2 Strength:

- 4.2.1 Principle: The average particle size of a sample is determined. The sample is then shaken for a definite time interval with steel balls and the final average particle size again determined. The strength, or resistance to abrasion, is the ratio of the final average particle size to the original.

An alternative strength measurement method may be used, provided that the accuracy of the alternative method is established by at least three replicate tests using the alternative method and the method described in section 4.2 of this standard. No alternative method shall be used if it does not provide the same strength values for all three replicate samples, within 2% of the strength value obtained using the method described in section 4.2.

4.2.2 Apparatus:

- 4.2.2.1 A W.S. Tyler Company Ro-Tap sieve shaking machine with sieves and special strength pan, or equivalent.
- 4.2.2.2 Six U.S. Standard Sieves, Nos. 4, 6, 8, 12, 16 and 20.
- 4.2.2.3 A special strength pan with a concave bottom. The pan may be constructed from a standard 8 in (203 mm) diameter Tyler pan (or equivalent) by replacing the bottom of the pan with a brass plate which has been turned 5/16 in (7.9 mm) thick at the circumference and tapers to 1/8 in (3.17 mm) thick in the center. The taper should be cut on a 43 in (1.09 m) radius and should extend from the center to the edge of the pan.
- 4.2.2.4 Twenty 1/2 in (12.7 mm) steel balls and ten 3/4 in (19 mm) steel balls.
- 4.2.2.5 A balance of 100 g capacity, accurate to 0.01 g.
- 4.2.3 Procedure:
- 4.2.3.1 Dry a 100 - 110 g sample for at least 6 h at 150°C.
- 4.2.3.2 Place 100 g of the sample on the top sieve of the six sieves. Shake the sieves for 10 min on the sieve shaker. Weigh the material remaining on each sieve. Compute the average particle size of the sample from the weighed average of each sieve fraction as in the following example:

Retained On	Mass, g	Mean Sieve Opening		Weighted Average	
No. 6 Sieve	22.8	X	4.01 mm	=	91.4
No. 8 Sieve	36.5	X	2.84 mm	=	103.7
No. 12 Sieve	24.1	X	2.00 mm	=	48.2
No. 16 Sieve	15.1	X	1.41 mm	=	21.3
No. 20 Sieve	0.9	X	1.00 mm	=	0.9
Pan	0.6	X	0.00 mm	=	0.0
					<u>265.5</u>

4.2.3.3 After the original particle size of the sample has been determined, combine the screen fractions and shake the whole sample on the shaker for 20 min in the special strength pan with the 30 steel balls. At the end of the 20-min shaking interval, pour the sample on the top nested sieve, remove the balls, and shake the sieves for 10 min as before to separate the screen fractions.

4.2.3.4 Weigh the carbon on each sieve and determine the average particle size as in paragraph 4.2.3.2.

4.2.4 Calculation:

$$\text{Strength} = \frac{\text{Final Average Particle Size}}{\text{Initial Average Particle Size}} \times 100$$

The phi (Ø) symbol is for the convenience of the user in locating areas where technical revisions have been made to the previous issue of the report. If the symbol is next to the report title, it indicates a complete revision of the report.

APPENDIX

A1. CARBON SIZE:

Experience has shown that commercial suppliers cannot consistently supply carbon which meets this SAE Standard. For this reason, it is suggested that the user perform the final sieving of the carbon to obtain samples for test use. The following commercially available "rough screened" carbon sieve analyses have proven to be satisfactory for final crushing and screening:

For Coarse Carbon:

SUPPLIERS COARSE CARBON ROUGH SCREEN
ANALYSIS SPECIFICATION

Retained on U.S. Standard Sieve No.	Mass %
8	0-10
12	40-60
16	30-40
20	0-10
Pan	0-1

For Fine Carbon:

SUPPLIERS FINE CARBON ROUGH SCREEN
ANALYSIS SPECIFICATION

Retained on U.S. Standard Sieve No.	Mass %
14	0-0.5
16	10-30
20	50-70
30	0-25
Pan	0-5

A2. CARBON FINAL SCREENING:

- A2.1 Coarse Carbon: A quantity of rough screened material may be sieved through a system of U.S. Standard Sieves 8, 12, and 16 (or their equivalent). Material retained on the No. 12 and No. 16 sieves is combined in the proportions specified under paragraph 3.3.2.

A2.2 Fine Carbon: A quantity of rough screen material may be sieved through a system of U.S. Standard Sieves 16, 20, and 30 (or their equivalent). Material retained on the 20 and 30 sieve is combined in the proportions specified under paragraph 3.3.1.

A2.3 Shaking: If a motorized vibrator shaker is used, material should be shaken in small quantities for approximately 10 minutes. If hand shaken, a longer shake period should be observed to assure that size segregation is complete.

A3. ALTERNATE STRENGTH DETERMINATION METHOD:

One alternate method which has been used to determine strength utilizes a cyclonic separator. This is acceptable if it provides equivalent strength, +2%, to the method described in 4.2.

A4. USED CARBON:

Current practice forbids the use of carbon more than once, though this requirement is not contained in this standard. Used carbon may be reused provided it is re-screened and meets all the requirements of this standard, and in addition, at least three replicate tests are made, using new and used carbon, with spark arresters with the same flow rating, +10%. The results of these replicate tests shall yield spark arrester efficiencies that are identical +5%, or the used carbon shall be rejected. Used carbon may be mixed with new carbon in a proportion up to one-third, without replicate testing, provided that the mixture meets all of the requirements of this standard.

A5. REFERENCE MATERIALS:

Refer to SAE J335, J342, and J350 for Spark Arrester Test Techniques. The standard screens used are described in ASTM E-11.