

D-90-17

~~NOTICE OF~~
ADOPTIONADOPTION NOTICE 1
17 October 1988 for
MA1520
July 1987

MA1520 was adopted on 17 October 1988 and is approved for use by the Department of Defense (DoD). Copies of this document are stocked by the DoD Single Stock Point, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120, for issue to DoD activities only. All other requestors must obtain documents from:

Society of Automotive Engineers, Inc.
400 Commonwealth Drive
Warrendale, PA 15096-0001

Title of Document: AREAS FOR CALCULATING STRESS OR LOAD
VALUES FOR METRIC MJ EXTERNALLY THREADED FASTENERS

Date of Specific Issue Adopted: July 1987

Releasing Non-Government Standards Body: Society of Automotive Engineers, Inc.

Custodians:

Army - AR
Air Force - 99

Military Coordinating Activity:

DLA - IS

(Project 53GP-0201)

Review Activities

Army - AV

FSC 53GP

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®

400 COMMONWEALTH DRIVE, WARRENDALE, PA 15096

METRIC AEROSPACE STANDARD

MA 1520

Issued 7-87

Submitted for recognition as an American National Standard

AREAS FOR CALCULATING STRESS OR LOAD VALUES FOR METRIC MJ EXTERNALLY THREADED FASTENERS

1. **PURPOSE:** This standard specifies the areas to be used in calculating stress or load values for use in metric externally threaded fastener procurement specifications and for information of designers.
2. **SCOPE:** Areas for the standard metric series of thread diameter-pitch combinations for aerospace externally threaded fasteners are established for the following conditions:
 - a) Area for ultimate shear stress or load in unthreaded shank.
 - b) Area for ultimate tensile stress or load in thread.
 - c) Area for stress durability test load in thread.
 - d) Area for stress-rupture test load at elevated temperature.
 - e) Area for tension-tension fatigue test load.
3. **REQUIREMENT:** The following areas are to be used in metric fastener procurement specifications for establishing the minimum mechanical properties which are specified in terms of allowable minimum test loads (unit stress rating times area). See Table I for calculated values.

3.1 Area for ultimate shear stress or load in fastener unthreaded shank.

For unthreaded shank greater than or less than thread nominal diameter, use maximum shank diameter for d in formula (1). For unthreaded shank equal to the thread nominal diameter, use basic major diameter of thread for d in formula (1). The calculated values for formula (1) in Table I are based on unthreaded shank equal to thread basic major diameter.

$$(1) A = 0.7854(d)^2$$

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Comments on this Standard are invited from interested parties and can be submitted in writing to SAE Headquarters.

3.2 Area for ultimate tensile stress or load in threaded portion.

3.2.1 Area for tensile stress or load in externally threaded fasteners with threads rolled after heat treatment and manufactured from alloy steels, corrosion and heat resistant steels and alloys, or titanium alloys, is based on the following empirical formula:

$$(2) \quad A = 0.7854(d_3)^2 \left[2 - \left(\frac{d_3}{d_2} \right)^2 \right]$$

where d_2 = maximum pitch diameter
 d_3 = maximum root diameter

Area based on the maximum pitch diameter, d_2 , is used as noted in 3.3 and 3.5 below.

$$(3) \quad A = 0.7854(d_2)^2$$

3.2.2 Area for tensile stress or load in externally threaded fasteners with threads rolled before heat treatment, or not rolled, is based on the mean diameter between maximum pitch diameter, d_2 , and the maximum root diameter, d_3 :

$$(4) \quad A = 0.7854[0.5(d_2 + d_3)]^2$$

3.3 Area for stress durability test load in thread.

Area based on formula (3). Test load is derived by using a percentage of the ultimate tensile stress as defined in the applicable procurement specification.

3.4 Area for stress-rupture test load at elevated temperature.

Area based on the maximum root diameter, d_3 .

$$(5) \quad A = 0.7854(d_3)^2$$

3.5 Area for tension-tension fatigue test load.

Area based on formula (3). High test load is derived by using a percentage of the ultimate tensile stress as defined in the procurement specification.

Low test load is 10% of high test load.

4. SYMBOLS: Thread symbols in formula are per MA 1370.