

AEROSPACE MATERIAL SPECIFICATION

SAE MAM 2223D

Issued	1982-07
Reaffirmed	1999-10
Noncurrent	2003-03
Cancelled	2008-01
Superseded by AMS 2223	

Tolerances, Metric Copper and Copper Alloy Seamless Tubing

RATIONALE

MAM 2223C has been designated Cancelled and Superseded because equivalent technical requirements are provided in AMS 2223.

CANCELLATION NOTICE

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of January, 2008, and has been superseded by AMS 2223. The requirements of the latest issue of AMS 2223 shall be fulfilled whenever reference is made to the cancelled MAM 2223C. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications, noting that it has been superseded by AMS 2223.

Cancelled specifications are available from SAE.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2008 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: **Tel:** 877-606-7323 (inside USA and Canada)
 Tel: 724-776-4970 (outside USA)
 Fax: 724-776-0790
 Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

1. SCOPE:

This specification covers established metric manufacturing tolerances applicable to copper and copper alloy seamless tubing ordered to metric (SI) dimensions. These tolerances apply to all conditions, unless otherwise noted. The term "exclusive" is used to apply only to the higher figure of a specified range.

1.1 AMS 2223 is the inch/pound version of this MAM.

2. DIAMETER:

See Table 1 and 2.1.

TABLE 1 - Average Diameter Tolerance

Specified Diameter mm			Average Diameter Tolerance mm, Plus and Minus
Up	to	3, incl	0.05
Over 3	to	16, incl	0.05
Over 16	to	25, incl	0.06
Over 25	to	50, incl	0.08
Over 50	to	75, incl	0.10
Over 75	to	100, incl	0.125
Over 100	to	125, incl	0.15
Over 125	to	150, incl	0.18
Over 150	to	200, incl	0.20
Over 200	to	250, incl	0.25

2.1 Applicable to inside or outside diameter. Table 1 is applicable to both refractory and non-refractory alloys.

2.2 Out-of roundness (difference between the major and minor diameters at any one cross-section) of unannealed tubing in straight lengths shall be not greater than specified in Table 2; if the tolerance is expressed as a percentage of a specified dimension, the tolerance so calculated shall be rounded to the nearest 0.025 millimeter to obtain the permissible tolerance.

TABLE 2 - Roundness Tolerance

Ratio of Specified Wall Thickness to Specified Diameter	Roundness Tolerance % of Specified Diameter
0.01 to 0.03, incl	1.5
Over 0.03 to 0.05, incl	1.0
Over 0.05 to 0.10, incl	0.8; 0.05 mm, min
Over 0.10	0.7; 0.05 mm, min

3. WALL THICKNESS:

When the tolerance is expressed as a percentage of a dimension, the tolerance so calculated shall be rounded to the nearest 0.025 millimeter to obtain the permissible tolerance.

3.1 Round; Non-Refractory:

See Table 3.

3.1.1 When round tube is ordered by outside and inside diameter, the maximum plus and minus deviation of the wall thickness from the nominal at any point shall not exceed the values given in the table by more than 50%.

3.1.2 Percent of specified wall expressed to the nearest 0.025 millimeter.

3.2 Round, Refractory:

See Table 4.

4. LENGTH:

See Table 5.

TABLE 3 - Wall Tolerance, Millimeter, Plus and Minus, Non-Refractory Rounds

Outside Diameter, mm (See 3.1.1) Wall Thickness, mm	Outside Diameter, mm (See 3.1.1) 0.80 to 3.0, incl	Outside Diameter, mm (See 3.1.1) Over 3.0 to 16, incl	Outside Diameter, mm (See 3.1.1) Over 16 to 25, incl	Outside Diameter, mm (See 3.1.1) Over 25 to 50, incl	Outside Diameter, mm (See 3.1.1) Over 50 to 100, incl	Outside Diameter, mm (See 3.1.1) Over 100 to 180, incl	Outside Diameter, mm (See 3.1.1) Over 180 to 250, incl
Up to 0.40, incl	0.05	0.03	0.04	0.05	---	---	---
Over 0.40 to 0.60, incl	0.08	0.05	0.05	0.06	---	---	---
Over 0.60 to 0.90, incl	0.08	0.06	0.06	0.08	0.10	---	---
Over 0.90 to 1.5, incl	0.08	0.08	0.09	0.09	0.12	0.20	---
Over 1.5 to 2.0, incl	---	0.09	0.10	0.10	0.15	0.20	0.25
Over 2.0 to 3.0, incl	---	0.10	0.12	0.12	0.20	0.20	0.28
Over 3.0 to 4.0, incl	---	0.12	0.15	0.15	0.20	0.25	0.30
Over 4.0 to 5.5, incl	---	0.20	0.20	0.20	0.25	0.30	0.35
Over 5.5 to 7.0, incl	---	---	0.25	0.25	0.30	0.35	0.45
Over 7.0 to 10, incl	---	---	0.30	5% (3.1.2)	5% (3.1.2)	6% (3.1.2)	6% (3.1.2)
Over 10	---	---	---	5% (3.1.2)	5% (3.1.2)	6% (3.1.2)	6% (3.1.2)

TABLE 4 - Wall Tolerance, Refractory Rounds

Specified Wall Thickness mm	Wall Tolerance, mm, Plus and Minus OD Ranges, mm 0.80 to 3.0, incl	Wall Tolerance, mm, Plus and Minus OD Ranges, mm Over 3.0 to 16, incl	Wall Tolerance, mm, Plus and Minus OD Ranges, mm Over 16 to 25, incl	Wall Tolerance, mm, Plus and Minus OD Ranges, mm Over 25 to 50, incl	Wall Tolerance, mm, Plus and Minus OD Ranges, mm, Over 50 to 100, incl	Wall Tolerance, mm, Plus and Minus OD Ranges, mm, Over 100 to 180, incl	Wall Tolerance, mm, Plus and Minus OD Ranges, mm, Over 180 to 250, incl
Up to 0.40, incl	0.06	0.04	0.05	0.06	---	---	---
0.40 to 0.60, incl	0.10	0.06	0.06	0.08	---	---	---
0.60 to 0.90, incl	0.10	0.08	0.08	0.10	0.13	---	---
0.90 to 1.5, incl	0.10	0.10	0.11	0.11	0.16	0.23	---
1.5 to 2.0, incl	---	0.11	0.13	0.13	0.19	0.25	0.33
2.0 to 3.0, incl	---	0.13	0.16	0.16	0.23	0.28	0.35
3.0 to 4.0, incl	---	0.18	0.18	0.19	0.25	0.33	0.38
4.0 to 5.5, incl	---	---	0.23	0.25	0.33	0.38	0.45
5.5 to 7.0, incl	---	---	0.30	0.33	0.38	0.45	0.50
7.0 to 10, incl	---	---	---	0.38	0.45	0.50	0.58
Over 10	---	---	---	6%	6%	8%	8%

TABLE 5 - Length Tolerances

Specified Diameter mm	Length Tolerance, mm, Plus Only Straight Lengths 150 mm and Under	Length Tolerance, mm, Plus Only Straight Lengths Over 150 to 600 mm, incl	Length Tolerance, mm, Plus Only Straight Lengths Over 600 to 2000 mm, incl	Length Tolerance, mm, Plus Only Straight Lengths Over 2000 to 4000 mm, incl	Length Tolerance, mm, Plus Only Straight Lengths Over 4000 mm	Length Tolerance, mm, Plus Only Coils 15,000 mm and Under	Length Tolerance, mm, Plus Only Coils Over 15,000 to 30,000 mm, incl
Up to 25, incl	0.80	1.5	2.5	6.0	12	300	600
Over 25 to 50, incl	1.5	2.5	3.0	6.0	12	300	600
Over 50 to 100, incl	1.6	2.4	3.1	6.0	12	--	--
Over 100	--	3.0	6.0	6.0	12	--	--

5. STRAIGHTNESS (UNANNEALED STRAIGHT TUBING 6.0 TO 100 MM OD):

See Table 6.

TABLE 6 - Straightness, Maximum Curvature

Length mm	Max Curvature (Depth of Arc) mm
Over 1000 to 2000, incl	5.0
Over 2000 to 2500, incl	8.0
Over 2500 to 3000, incl	12
Over 3000	12 in any 3000 mm of total length